

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



**COLUMBIA**  
COATINGS

|                |                       |
|----------------|-----------------------|
| <b>Number:</b> | RAL6021               |
| <b>Name:</b>   | RAL 6021 – Pale Green |
| <b>Type:</b>   | TGIC                  |

## Powder Properties

|                              |                                |
|------------------------------|--------------------------------|
| <b>Specific Gravity</b>      | Approx. 1.55 g/cm <sup>3</sup> |
| <b>Storage Temp</b>          | < 80°F (27°C)                  |
| <b>Theoretical Coverage</b>  | 124 sq. ft/lb. @ 1 mil         |
| <b>Particle Distribution</b> | n/a                            |

## Coating Properties

|                        |  |
|------------------------|--|
| <b>Film Thickness</b>  | Recommended Film Thickness: 2–3 mils                           |
| <b>Cure Schedule</b>   | Metal Temperature:<br>10 minutes at 400°F (204°C)              |
| <b>Gloss Level</b>     | 80% @ 60°  |
| <b>Pencil Hardness</b> | 2H (ASTM D3363)  |
| <b>Flexibility</b>     | 1/8" (ASTM D522) (Conical Mandrel)                             |
| <b>Adhesion</b>        | 5B (ASTM D3359)  |
| <b>Direct Impact</b>   | 100 in-lb. direct (ASTM D2794)                                 |
| <b>Reverse Impact</b>  | 100 in-lb. direct (ASTM D2794)                                 |
| <b>Salt Spray</b>      | 1000 Hrs. Pass <1/8" Scribe Creep<br>- No Blisters (ASTM B117) |

[www.columbiacoatings.com](http://www.columbiacoatings.com)