

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 February 2012 (02.02.2012)

PCT

(10) International Publication Number
WO 2012/015573 A1

(51) International Patent Classification:

C08L 23/08 (2006.01) *C10M 143/04* (2006.01)
C08L 23/14 (2006.01)

KOLB, Rainer [DE/US]; 3411 Park Spring Lane, Kingwood, TX 77345 (US).

(21) International Application Number:

PCT/US2011/043190

(74) Agents: **LIN, Hsin** et al.; Exxonmobil Chemical Company, Law Technology, P.O. Box 2149, Baytown, TX 77522-2149 (US).

(22) International Filing Date:

7 July 2011 (07.07.2011)

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/368,473	28 July 2010 (28.07.2010)	US
13/006,042	13 January 2011 (13.01.2011)	US
13/006,057	13 January 2011 (13.01.2011)	US
11156622.0	2 March 2011 (02.03.2011)	EP

(71) Applicant (*for all designated States except US*): **EXXONMOBIL CHEMICAL PATENTS INC.** [US/US]; 5200 Bayway Drive, Baytown, TX 77520-2101 (US).

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **DATTA, Sudhin** [US/US]; 315 E. Cowan Drive, Houston, TX 77007 (US). **FARNG, Liehpao, O.** [US/US]; 22 Evans Lane, Lawrenceville, NJ 08648 (US). **MINAK-BERNERO, Vera** [US/US]; 945 Papen Road, Bridgewater, NJ 08807 (US). **SIROTA, Eric, B.** [US/US]; 106 Bertron Road, Flemington, NJ 08822 (US). **SMIRNOVA, Diana** [US/US]; 5 Stillwell Road, High Bridge, NJ 08829 (US).

Published:

— with international search report (Art. 21(3))

(54) Title: VISCOSITY MODIFIERS COMPRISING BLENDS OF ETHYLENE-BASED COPOLYMERS

(57) Abstract: The present invention is directed to polymer blend compositions for use as viscosity modifiers comprising at least three ethylene-based copolymer components. The viscosity modifiers described herein comprise a first ethylene-based copolymer having an ethylene content of from about 35 to about 55 wt% and/or a heat of fusion of from about 0 to about 30 J/g, a second ethylene-based copolymer having an ethylene content of from about 55 to about 85 wt% and/or a heat of fusion of from about 30 to about 50 J/g, and a third ethylene-based copolymer having an ethylene content of from about 65 to about 85 wt% and/or a heat of fusion of from about 40 to about 70 J/g. The invention is also directed to lubricant compositions comprising a lubricating base-stock and a polymer blend as described herein.



WO 2012/015573 A1

TITLE: VISCOSITY MODIFIERS COMPRISING BLENDS OF ETHYLENE-BASED COPOLYMERS

Inventors: Sudhin Datta, Liehpao O. Farng, Vera Minak-Bernero, Eric B. Sirota, Diana
5 Smirnova, Rainer Kolb

PRIORITY CLAIM

[0001] This application claims the benefit of and priority to U.S. Patent Application
Serial No. 13/006,042 (2011EM004), filed January 13, 2011, EP Application No.
11156622.0, filed March 2, 2011, U.S. Patent Application Serial No. 13/006,057
10 (2011EM003), filed January 13, 2011, and U.S. Provisional Application Serial No.
61/368,473 (2010EM216), entitled "Discrete Ethylene-Based Copolymers as Viscosity
Modifiers" and filed July 28, 2010, which are incorporated by reference herein in their
entirety.

FIELD OF THE INVENTION

15 [0002] The present invention relates to polymer blends useful as rheology modifiers.
More particularly, the invention relates to compositionally disperse and/or crystallinity
disperse polymer blends that are useful in modifying the rheological properties of fluids,
wherein the individual components of the polymer blend have large differences in
crystallinity and include at least one component having no observable crystallinity.

BACKGROUND OF THE INVENTION

20 [0003] Lubrication fluids are applied between moving surfaces to reduce friction, thereby
improving efficiency and reducing wear. Lubrication fluids also often function to dissipate
the heat generated by moving surfaces.

[0004] One type of lubrication fluid is a petroleum-based lubrication oil used for internal
25 combustion engines. Lubrication oils contain additives that help the lubrication oil to have a
certain viscosity at a given temperature. In general, the viscosity of lubrication oils and fluids
is inversely dependent upon temperature. When the temperature of a lubrication fluid is
increased, the viscosity generally decreases, and when the temperature is decreased, the
viscosity generally increases. For internal combustion engines, for example, it is desirable to
30 have a lower viscosity at low temperatures to facilitate engine starting during cold weather,
and a higher viscosity at higher ambient temperatures when lubrication properties typically
decline.

[0005] Additives for lubrication fluids and oils include rheology modifiers, such as
viscosity index (VI) improvers. VI improving components, many of which are derived from

ethylene-alpha-olefin copolymers, modify the rheological behavior of a lubricant to increase viscosity and promote a more constant viscosity over the range of temperatures at which the lubricant is used. Higher ethylene content copolymers efficiently promote oil thickening and shear stability. However, higher ethylene content copolymers also tend to flocculate or aggregate in oil formulations leading to extremely viscous and, in the limit, solid formulations. Flocculation typically happens at ambient or subambient conditions of controlled and quiescent cooling. This deleterious property of otherwise advantageous higher ethylene content viscosity improvers is measured by low temperature solution rheology. Various remedies have been proposed for these higher ethylene content copolymer formulations to overcome or mitigate the propensity towards the formation of high viscosity flocculated materials.

[0006] It is anticipated that the performance of VI improvers can be substantially improved, as measured by the thickening efficiency (TE) and the shear stability index (SSI), by appropriate and careful manipulation of the structure of the VI improver. Particularly, it has been discovered that performance improves when the distribution of the monomers and the chain architecture are controlled and segregated into at least three compositionally disperse and/or crystallinity disperse polymeric populations. These disperse polymeric populations may be achieved by the use of a synthesis process that employs metallocene-based catalysts in the polymerization process.

[0007] One proposed solution is the use of blends of amorphous and semi-crystalline ethylene-based copolymers for lubricant oil formulations. The combination of two such ethylene-propylene copolymers allows for increased thickening efficiency, shear stability index, low temperature viscosity performance and pour point. See, e.g., U.S. Patent Nos. 7,402,235 and 5,391,617, and European Patent 0 638,611, the disclosures of which are incorporated herein by reference.

[0008] There remains a need, however, for novel rheology modifier compositions comprised of ethylene and alpha-olefin-based comonomers suitable for use in VI improvers which have unexpectedly high thickening efficiency compared to prior compositions while still being equivalent in their beneficial low temperature solution rheology properties. The present invention meets this and other needs. The combined components of the invention deliver a viscosity modifier which does not show an adverse effect on viscosity due to lowering the temperature from ambient to -35°C in solution in synthetic and petroleum basestocks.

[0009] Contrary to the teachings of the prior art, it has been found that there is a preferred relationship between the amount and composition of the discrete distributions of the ethylene-based alpha-olefin copolymers used in the polymeric blends for VI improvers. This relationship leads to ethylene-based alpha-olefin copolymers having a distribution of at least three individual ethylene-based copolymers with C₃-C₂₀ alpha olefin comonomers. Each of the individual ethylene-based copolymers (hereinafter components) is a single copolymer made in a single polymerization environment having a predefined composition and molecular weight. In one or more embodiments, each of the components is a most probable distribution of molecular weights. The components differ in their molecular weight and composition. The invention describes the combination of these polymers in a predetermined weight ratio such that the least crystalline polymer (typically one with the lowest wt% ethylene in the composition of the component) is present in an amount of from about 15 to about 85 wt%, based on the total weight of the combination. The balance of the composition comprises two components with greater crystallinity and thus a higher wt% ethylene in the composition of the components.

[0010] The present invention describes the ranges of the composition and crystallinity for the components of the viscosity modifier. In some embodiments of the invention, the first and second components, when they are copolymers of ethylene and propylene, are separated by no less than 18 wt% ethylene content and the second and third components are separated by no less than 5 wt% ethylene content. In addition, the least crystalline polymer has an ethylene content less than 55 wt%, preferably less than 53 wt%.

SUMMARY OF THE INVENTION

[0011] The present invention is directed to polymer blend compositions for use as viscosity modifiers comprising at least three ethylene-based copolymer components. The viscosity modifiers described herein comprise a first ethylene-based copolymer having an ethylene content of from about 35 to about 55 wt% and/or a heat of fusion of from about 0 to about 30 J/g, a second ethylene-based copolymer having an ethylene content of from about 55 to about 85 wt% and/or a heat of fusion of from about 30 to about 50 J/g, and a third ethylene-based copolymer having an ethylene content of from about 65 to about 85 wt% and/or a heat of fusion of from about 40 to about 70 J/g. The invention is also directed to lubricant compositions comprising a lubricating basestock and a polymer blend as described herein.

DETAILED DESCRIPTION OF THE INVENTION

[0012] The present invention relates to polymer blends comprising polymer components including, but not limited to, compositionally disperse ethylene-based copolymers and/or crystallinity disperse ethylene-based copolymers that are useful in modifying the rheological properties of lubrication fluids. The compositionally disperse polymer blends are formed from at least three discrete compositions of ethylene-based copolymers. The crystallinity disperse polymer blends are formed from ethylene-based copolymers having at least three discrete values of residual crystallinity.

[0013] The performance of ethylene-based rheology modifiers as viscosity index (VI) improvers are measured by the thickening efficiency (TE) and the shear stability index (SSI), particularly by the ratio of TE to SSI. It is generally believed that the composition of an olefin copolymer at a given SSI largely determines the TE, and that higher ethylene content is preferred because of its inherent TE. While increasing the ethylene content of rheology modifiers leads to improved TE/SSI ratios, it also leads to increasing crystallinity of the olefin copolymer. Increasing crystallinity, however, detracts from the performance of a rheology modifier as a VI improver because crystalline polymers tend to flocculate, either by themselves or in association with other components of the lubrication oil, and precipitate out of lubrication oils. These precipitates are apparent as regions (e.g., "lumps") of high viscosity or essentially complete solidification (e.g., "gels") and can lead to clogs and blockages of pumps and other passageways for the lubrication fluid and can harm and in some cases cause failure of moving machinery.

[0014] While not wishing to be bound by any particular theory, it is believed that rheology modifiers for lubrication fluids comprising ethylene-based copolymers which are compositionally disperse and/or crystallinity disperse will be less prone to the deleterious effects of macroscopic crystallization in dilute solution, as measured by the change in the rheology of the fluid solution compared to an equivalent amount of a single ethylene-based copolymer of the same average composition as the disperse blend. It is also believed that these compositionally and/or crystallinity disperse components will have lower crystallization on cooling from ambient to sub-ambient temperatures, resulting in better low temperature flow properties in solution as compared to equivalent compositionally uniform polymers of similar molecular weight and thickening efficiency. These polymer blends and their use in lubrication oil compositions with basestocks can be distinguished from other compositionally non-disperse olefin copolymers by physical separation of the compositionally disperse

polymer blend into components as well as by a higher ratio of the melting point by DSC to the heat of fusion than would be observed for a non-disperse polymer of the same average ethylene content, melt viscosity, and composition.

[0015] This invention is directed to a selection of blend compositions for use as viscosity
5 modifiers comprising at least three ethylene-based copolymer components. The viscosity
modifiers described herein comprise a first ethylene-based copolymer having an ethylene
content of from about 35 to about 55 wt% and/or a heat of fusion of from about 0 to about 30
J/g, a second ethylene-based copolymer having an ethylene content of from about 55 to about
85 wt% and/or a heat of fusion of from about 30 to about 50 J/g, and a third ethylene-based
10 copolymer having an ethylene content of from about 65 to about 85 wt% and/or a heat of
fusion of from about 40 to about 70 J/g greater than that of the second copolymer. The three
copolymers all have a weight average molecular weight (Mw) less than or equal to about
130,000, and MIA/MIB and MIA/MIC are both less than or equal to about 3.0. The
invention is also directed to lubricant compositions comprising a lubricating basestock and a
15 polymer blend as described herein.

Definitions

[0016] For purposes of this invention and the claims herein, the definitions set forth
below are used.

[0017] As used herein, the term "complex viscosity" means a frequency-dependent
20 viscosity function determined during forced small amplitude harmonic oscillation of shear
stress, in units of Pascal-seconds, that is equal to the difference between the dynamic
viscosity and the out-of-phase viscosity (imaginary part of complex viscosity).

[0018] As used herein, the term "Composition Distribution Breadth Index" (CDBI) is as
defined in U.S. Patent No. 5,382,630, which is incorporated by reference herein. CDBI is
25 defined as the weight percent of the copolymer molecules having a comonomer content
within 50% of the median total molar comonomer content. The CDBI of a copolymer is
readily determined utilizing well known techniques for isolating individual fractions of a
sample of the copolymer. One such technique is Temperature Rising Elution Fraction
(TREF), as described in L. Wild, et al., J. Poly. Sci., Poly. Phys. Ed., Vol. 20, p. 441 (1982)
30 and U.S. Patent No. 5,008,204, both of which are incorporated herein by reference.

[0019] As used herein, the term "compositionally disperse" means a polymer blend
comprised of at least three discrete compositions of ethylene-based copolymers.

[0020] As used herein, the term "copolymer" includes any polymer having two or more monomers.

[0021] As used herein, the term "crystallinity disperse" means a polymer blend comprised of at least three ethylene-based copolymers having discrete values of residual crystallinity.

5 [0022] As used herein, the term "disperse" means that the compositions include constituent polymer fractions which have different compositions and/or different crystallinity due, in part, to different molecular weight distributions and/or different monomer compositional or sequence distributions.

10 [0023] As used herein, the term "EA" means the weight percent of ethylene-derived units in the first ethylene-based copolymer based on the weight of the first ethylene-based copolymer.

[0024] As used herein, the term "EB" means the weight percent of ethylene-derived units in the second ethylene-based copolymer based on the weight of the second ethylene-based copolymer.

15 [0025] As used herein, the term "EC" means the weight percent of ethylene-derived units in the third ethylene-based copolymer based on the weight of the third ethylene-based copolymer.

[0026] As used herein, the term "ethylene-based copolymer" means a copolymer comprised of ethylene and one or more C₃-C₂₀ comonomers.

20 [0027] As used herein, the term "HA" means the heat of fusion in units of joules/gram on a first melt of the first ethylene-based copolymer.

[0028] As used herein, the term "HB" means the heat of fusion in units of joules/gram on the first melt of the second ethylene-based copolymer.

25 [0029] As used herein, the term "HC" means the heat of fusion in units of joules/gram on the first melt of the third ethylene-based copolymer.

[0030] As used herein, the term "intermolecular composition distribution," (also "InterCD" or "intermolecular CD"), defines the compositional heterogeneity in terms of ethylene content, among polymer chains. It is expressed as the minimum deviation, analogous to a standard deviation, in terms of weight percent ethylene from the average
30 ethylene composition for a given copolymer sample needed to include a given weight percent of the total copolymer sample, which is obtained by excluding equal weight fractions from both ends of the distribution. The deviation need not be symmetrical. When expressed as a single number, for example, an intermolecular composition distribution of 15 wt% shall mean

the larger of the positive or negative deviations. For example, at 50 wt% intermolecular composition distribution the measurement is akin to conventional composition distribution breadth index.

[0031] As used herein, the term "intramolecular composition distribution" (also "IntraCD" or "intramolecular CD") defines the compositional variation, in terms of ethylene, within a copolymer chain. It is expressed as the ratio of the alpha-olefin to ethylene along the segments of the same chain.

[0032] As used herein, the term "MIA" means the melt index, in units of g/10 min or dg/min, of the first ethylene-based copolymer.

[0033] As used herein, the term "MIB" means the melt index, in units of g/10 min or dg/min, of the second ethylene-based copolymer.

[0034] As used herein, the term "MIC" means the melt index, in units of g/10 min or dg/min, of the third ethylene-based copolymer.

[0035] As used herein, the term "MnA" means the number-average molecular weight of the first ethylene-based copolymer, as measured by GPC.

[0036] As used herein, the term "MnB" means the number-average molecular weight of the second ethylene-based copolymer, as measured by GPC.

[0037] As used herein, the term "MnC" means the number-average molecular weight of the third ethylene-based copolymer, as measured by GPC.

[0038] As used herein, the term "MwA" means the weight-average molecular weight of the first ethylene-based copolymer in units of grams/mole in terms of polystyrene, as measured by GPC.

[0039] As used herein, the term "MwB" means the weight-average molecular weight of the second ethylene-based copolymer in units of grams/mole in terms of polystyrene, as measured by GPC.

[0040] As used herein, the term "MwC" means the weight-average molecular weight of the third ethylene-based copolymer in units of grams/mole in terms of polystyrene, as measured by GPC.

[0041] As used herein, the term "MWD" means the molecular weight distribution, or ratio of weight-average molecular weight (Mw) to number-average molecular weight (Mn).

[0042] As used herein, the term "melting point" means the highest peak among principal and secondary melting peaks as determined by DSC during the second melt, as discussed in further detail below.

[0043] As used herein, the term "polyene" means monomers or polymers having two or more unsaturations, e.g., dienes, trienes, and the like.

[0044] As used herein, the term "polypropylene" means a polymer made of at least 50% propylene units, preferably at least 70% propylene units, more preferably at least 80% propylene units, even more preferably at least 90% propylene units, even more preferably at least 95% propylene units or 100% propylene units.

[0045] As used herein, the term "substantially linear structure" means a polymer characterized as having less than 1 branch point pendant with a carbon chain larger than 19 carbon atoms per 200 carbon atoms along a backbone.

[0046] For purposes of this specification and the claims appended thereto, when a polymer or copolymer is referred to as comprising an olefin, including, but not limited to ethylene, propylene, and butene, the olefin present in such polymer or copolymer is the polymerized form of the olefin. For example, when a copolymer is said to have an "ethylene" content of 35-55 wt%, it is understood that the mer unit in the copolymer is derived from ethylene in the polymerization reaction and said derived units are present at 35-55 wt%, based upon the weight of the copolymer.

Polymer blends

[0047] In some embodiments of the invention, the rheology modifiers for lubrication fluids described herein comprise compositionally disperse polymer blends and/or crystallinity disperse polymer blends. These polymer blends comprise a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer. Unless otherwise specified, all references to first ethylene-based copolymer, second ethylene-based copolymer, and third ethylene-based copolymer refer to both compositionally disperse polymer blends and crystallinity disperse polymer blends.

[0048] The first ethylene-based copolymer, having a relatively lower ethylene content, is a copolymer of ethylene, an alpha-olefin comonomer, and optionally an internal olefin and optionally a polyene, such as a diene.

[0049] The second ethylene-based copolymer, having a relatively higher ethylene content, is a copolymer of ethylene, an alpha-olefin and optionally an internal olefin and optionally a polyene, such as a diene.

[0050] The third ethylene-based copolymer, having a relatively higher still ethylene content, is a copolymer of ethylene, an alpha-olefin and optionally an internal olefin and optionally a polyene, such as a diene.

[0051] The polymer blends of the invention comprise from about 15 to about 85 wt% of a first ethylene-based copolymer, with the balance of the blend comprising a second ethylene-based copolymer and a third ethylene-based copolymer. In some embodiments, the blend comprises from about 25 to about 75 wt% of the first ethylene-based copolymer and from
5 about 25 to about 75 wt% of a combination of the second and the third ethylene-based copolymers. In further embodiments, the blend comprises from about 35 to about 65 wt% of the first ethylene-based copolymer and from about 35 to about 65 wt% of a combination of the second and the third ethylene-based copolymers.

[0052] For compositionally disperse polymer blends, the first ethylene-based copolymer
10 is characterized by an ethylene weight percent (EA).

[0053] For crystallinity disperse polymer blends, the first ethylene-based copolymer is characterized by a heat of fusion (HA).

[0054] The first ethylene-based copolymer may be further characterized by a melt index (MIA), a number-average molecular weight (MnA), and a weight-average molecular weight
15 (MwA).

[0055] In some embodiments, the EA of the first ethylene-based copolymer (in wt%) is in the range of about $35 \leq EA \leq 55$, or about $40 \leq EA \leq 55$, or about $45 \leq EA \leq 53$, or about $47 \leq EA \leq 52$.

[0056] In the same or other embodiments, the HA of the first ethylene-based copolymer
20 (in J/g) is in the range of about $0 \leq HA \leq 30$, or about $0 \leq HA \leq 15$, or about $0 \leq HA \leq 10$, or about $0 \leq HA \leq 5$. In some other embodiments, the HA of the first ethylene-based copolymer is about 2 J/g.

[0057] For compositionally disperse polymer blends, the second ethylene-based copolymer is characterized by an ethylene weight percent (EB).

25 [0058] For crystallinity disperse polymer blends, the second ethylene-based copolymer is characterized by a heat of fusion (HB).

[0059] The second ethylene-based copolymer may be further characterized by a melt index (MIB), a number-average molecular weight (MnB), and a weight-average molecular weight (MwB).

30 [0060] In some embodiments, the EB of the second ethylene-based copolymer (in wt%) is in the range of about $35 \leq EB \leq 75$, or about $55 \leq EB \leq 73$, or about $65 \leq EB \leq 73$, or about $67 \leq EB \leq 72$, or about $67 \leq EB \leq 71$.

[0061] In the same or other embodiments, the HB of the second ethylene-based copolymer (in J/g) is in the range of about $30 < HB \leq 50$, or about $35 < HB \leq 50$, or about $40 < HB \leq 48$. In some other embodiments, the HB of the second ethylene-based copolymer is about 45.

5 [0062] In some embodiments of the compositionally disperse polymer blend, the ethylene weight percent EA of the first ethylene-based copolymer may be less than the ethylene weight percent EB of the second ethylene-based copolymer.

[0063] In some embodiments, the compositionally disperse polymer blends may be characterized by the difference in the ethylene weight percent between the second and first
10 ethylene-based copolymers, EB and EA. In some embodiments, $EB - EA \geq 12$, or $EB - EA \geq 17$, or $EB - EA \geq 21$, or $EB - EA \geq 23$. In some embodiments, the difference in ethylene weight percent, EB and EA, is in the range of about $17 \leq EB - EA \leq 23$.

[0064] For compositionally disperse polymer blends, the third ethylene-based copolymer is characterized by an ethylene weight percent (EC).

15 [0065] For crystallinity disperse polymer blends, the third ethylene-based copolymer is characterized by a heat of fusion (HC).

[0066] In some embodiments, the EC of the third ethylene-based copolymer (in wt%) is in the range of about $65 \leq EC \leq 85$, or about $70 \leq EC \leq 85$, or about $71 \leq EC \leq 85$, or about $72 \leq EC \leq 83$, or about $73 \leq EC \leq 81$.

20 [0067] In the same or other embodiments, the HC of the third ethylene-based copolymer (in J/g) is in the range of about $40 \leq HC \leq 85$, or about $50 \leq HC \leq 80$, or about $55 \leq HC \leq 75$, or about $60 \leq HC \leq 75$, or about $65 \leq HC \leq 75$.

[0068] In some embodiments of the compositionally disperse polymer blend, the ethylene weight percent EB of the second ethylene-based copolymer may be less than the ethylene
25 weight percent EC of the third ethylene-based copolymer.

[0069] In some embodiments, the compositionally disperse polymer blends may be characterized by the difference in the ethylene weight percent between the third and second ethylene-based copolymers, EC and EB. In some embodiments, $EC - EB \geq 4$, or $EC - EB \geq 6$, or $EC - EB \geq 8$, or $EC - EB \geq 10$. In some embodiments, the difference in ethylene weight
30 percent, EC and EB, is in the range of $5 \leq EC - EB \leq 10$.

[0070] In some embodiments of the crystallinity disperse polymer blends, the heat of fusion HB of the second ethylene-based copolymer may be less than the heat of fusion HC of the third ethylene-based copolymer.

[0071] In some embodiments, the crystallinity disperse polymer blends may be characterized by the difference in the first melt heats of fusion of the third and second ethylene-based copolymers, HC and HB. In some embodiments, $HC - HB \geq 4$, or $HC - HB \geq 8$, or $HC - HB \geq 12$, or $HC - HB \geq 16$. In some embodiments, the difference in the heats of fusion, HC and HB, is in the range of about $8 \leq HC - HB \leq 10$.

[0072] The compositionally disperse and/or crystallinity disperse polymer blends may be further characterized by the ratio of the melt index of the second ethylene-based copolymer to the melt index of the third ethylene-based copolymer, MIB/MIC. In some embodiments, MIB/MIC is less than or equal to 3, less than or equal to 2, or less than or equal to 1.

[0073] The compositionally disperse and/or crystallinity disperse polymer blends may be further characterized by the absolute value of the difference in the melt index of the third ethylene-based copolymer, MIC, and the melt index of the second ethylene-based copolymer, MIB. In some embodiments, $|MIC - MIB| \leq 3.0$, or $|MIC - MIB| \leq 2.5$, or $|MIC - MIB| \leq 2.0$, or $|MIC - MIB| \leq 1.5$, or $|MIC - MIB| \leq 1.1$, or $|MIC - MIB| \leq 1.0$.

[0074] The first, second, and third ethylene-based copolymers may be characterized by a weight-average molecular weight (M_wA , M_wB , and M_wC , respectively) of less than or equal to 130,000, or less than 120,000, or less than 110,000, or less than 100,000, or less than 90,000, or less than 80,000, or less than 70,000. Preferably, M_wA , M_wB , and/or M_wC are from 70,000 to 95,000.

[0075] The first, second, and third ethylene-based copolymers may be characterized by a molecular weight distribution (MWD). Each of the first, second, and third ethylene-based copolymers has an MWD of less than 3.0, or less than 2.4, or less than 2.2, or less than 2.0. Preferably, the MWD of each copolymer is from about 1.80 to about 1.95.

[0076] The MFR of the compositionally disperse and/or crystallinity disperse polymer blends will be intermediate to the MFR of the lower and higher ethylene content copolymers when these copolymers have different MFRs. In some embodiments of the present invention, the first, second, and third ethylene-based copolymers each have an MFR of from about 0.2 to about 25.

[0077] The first, second, and third ethylene-based copolymers each comprise ethylene and one or more comonomers. The comonomers are selected from the group consisting of C_3 to C_{20} alpha-olefins and mixtures thereof. Preferably, the comonomer in each copolymer is propylene, butene, hexene, octene, or mixtures thereof.

[0078] In some embodiments, the first, second, or third ethylene-based copolymers may each further comprise a polyene monomer. In such embodiments, each copolymer may further comprise up to 5 mole%, up to 4 mole%, up to 3 mole%, up to 2 mole%, or up to 1 mole% polyene-derived units.

5 [0079] In some embodiments, the first, second, and/or third ethylene-based copolymer comprises one or more polymer fractions having a different Mn, a different Mw, or a different MWD.

[0080] In some embodiments, the first, second, and/or third ethylene-based copolymers may have different comonomer insertion sequences.

10 [0081] In some embodiments, the first, second, and/or third ethylene-based copolymer of a compositionally disperse polymer blend has a substantially linear structure.

[0082] The substantially linear structure of the first, second, and/or third ethylene-based copolymer has less than 1 branch point pendant with a carbon chain larger than 19 carbon atoms per 200 carbon atoms along a backbone, less than 1 branch point pendant with a carbon chain larger than 19 carbon atoms per 300 branch points, less than 1 branch point pendant with a carbon chain larger than 19 carbon atoms per 500 carbon atoms, or less than 1 branch point pendant with a carbon chain larger than 19 carbon atoms per 1000 carbon atoms, notwithstanding the presence of branch points due to incorporation of the comonomer.

15 [0083] The discrete ethylene-based copolymers can be combined such that the first ethylene-based copolymer, which is the least crystalline ethylene-based copolymer (and typically the ethylene-based copolymer with the lowest wt% ethylene) can be present in an amount of from about 15 to about 85 wt%, based on the combined weight of the first, second, and third ethylene-based copolymers, with the second and third ethylene-based copolymers together comprising the balance of the blend. In one or more embodiments, the first ethylene-based copolymer can be present in an amount from about 25 to about 75 wt%, or about 35 to about 65 wt%, based on the total weight of the first, second, and third copolymers.

20 [0084] The polymer blend can have an overall concentration or content of ethylene-derived units ranging from about 70 mole% to about 85 mole%. For example, the polymer blend can have a concentration of ethylene-derived units ranging from a low of about 70 mole%, about 72 mole%, or about 74 mole% to a high of about 78 mole%, about 80 mole%, about 83 mole%, or about 85 mole%. The MFR of the polymer blend can be intermediate to the MFR of the lowest and highest ethylene content copolymers when the copolymers have different MFRs.

Comonomer Components

[0085] Suitable comonomers include, but are not limited to, propylene (C₃) and other alpha-olefins, such as C₄ to C₂₀ alpha-olefins (also referred to herein as " α -olefins"), and preferably propylene and C₄ to C₁₂ α -olefins. The α -olefin comonomer can be linear or
5 branched, and two or more comonomers can be used, if desired. Thus, reference herein to "an alpha-olefin comonomer" includes one, two, or more alpha-olefin comonomers.

[0086] Examples of suitable comonomers include propylene, linear C₄ to C₁₂ α -olefins, and α -olefins having one or more C₁ to C₃ alkyl branches. Specific examples include: propylene; 1-butene; 3-methyl-1-butene; 3,3-dimethyl-1-butene; 1-pentene; 1-pentene with
10 one or more methyl, ethyl or propyl substituents; 1-hexene with one or more methyl, ethyl or propyl substituents; 1-heptene with one or more methyl, ethyl, or propyl substituents; 1-octene with one or more methyl, ethyl, or propyl substituents; 1-nonene with one or more methyl, ethyl, or propyl substituents; ethyl, methyl, or dimethyl-substituted 1-decene, or 1-dodecene. Preferred comonomers include: propylene., 1-butene; 1-pentene; 3-methyl-1-
15 butene; 1-hexene; 3-methyl-1-pentene; 4-methyl-1-pentene; 3,3-dimethyl-1-butene; 1-heptene; 1-hexene with a methyl substituents on any of C₃ to C₅; 1-pentene with two methyl substituents in any stoichiometrically acceptable combination on C₃ or C₄; 3-ethyl-1-pentene; 1-octene; 1-pentene with a methyl substituents on any of C₃ or C₄; 1-hexene with two methyl substituents in any stoichiometrically acceptable combination on C₃ to C₅; 1-pentene with
20 three methyl substituents in any stoichiometrically acceptable combination on C₃ or C₄; 1-hexene with an ethyl substituents on C₃ or C₄; 1-pentene with an ethyl substituents on C₃ and a methyl substituents in a stoichiometrically acceptable position on C₃ or C₄; 1-decene; 1-nonene; 1-nonene with a methyl substituents on any of C₃ to C₉; 1-octene with two methyl substituents in any stoichiometrically acceptable combination on C₃ to C₇; 1-heptene with
25 three methyl substituents in any stoichiometrically acceptable combination on C₃ to C₆; 1-octene with an ethyl substituents on any of C₃ to C₇; 1-hexene with two ethyl substituents in any stoichiometrically acceptable combination on C₃ or C₄; and 1-dodecene.

[0087] Other suitable comonomers can include internal olefins. Preferred internal olefins are cis 2-butene and trans 2-butene. Other internal olefins are contemplated. When an
30 internal olefin is present, negligible amounts, such as about 2 wt% or less of the total amount of the internal olefin, can be present in the low ethylene-content copolymer, and most of the

internal olefin, such as about 90 wt% or more of the total amount of the internal olefin, can be present in the high ethylene-content copolymer.

[0088] Suitable comonomers can also include one or more polyenes. Suitable polyenes can include non-conjugated dienes, preferably those that are straight chain, hydrocarbon di-
5 olefins or cycloalkenyl-substituted alkenes, having about 6 to about 15 carbon atoms, for example: (a) straight chain acyclic dienes, such as 1,4-hexadiene and 1,6-octadiene; (b) branched chain acyclic dienes, such as 5-methyl-1, 4-hexadiene, and 3,7-dimethyl-1,6; (c) single ring alicyclic dienes, such as 1,4-cyclohexadiene, 1,5-cyclo-octadiene, and 1,7-cyclododecadiene; (d) multi-ring alicyclic fused and bridged ring dienes, such as
10 tetrahydroindene, norbornadiene, methyl-tetrahydroindene, dicyclopentadiene (DCPD), bicyclo-(2.2.1)-hepta-2,5-diene, alkenyl, alkylidene, cycloalkenyl and cycloalkylidene norbornenes, such as 5-methylene-2-norbornene (MNB), 5-propenyl-2-norbornene, 5-isopropylidene-2-norbornene, 5-(4-cyclopentenyl)-2-norbornene, 5-cyclohexylidene-2-norbornene, and 5-vinyl-2-norbornene (VNB); and (e) cycloalkenyl-substituted alkenes, such
15 as vinyl cyclohexene, allyl cyclohexene, vinyl cyclooctene, 4-vinyl cyclohexene, allyl cyclodecene; and vinyl cyclododecene. Of the non-conjugated dienes typically used, the preferred dienes are dicyclopentadiene (DCPD); 1,4-hexadiene; 1,6-octadiene; 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; 5-methylene-2-norbornene; 5-ethylidene-2-norbornene (ENB); and tetracyclo (Δ -11,12) 5,8 dodecene. It is preferred to use dienes that
20 do not lead to the formation of long chain branches, and non- or lowly branched polymer chains are preferred. Other polyenes that can be used include cyclopentadiene and octatetraene; and the like.


[0089] When a polyene is present, the ethylene-based copolymers can include up to 5 mole%, up to 4 mole%, up to 3 mole%, up to 2 mole%, and up to 1 mole% polyene-derived
25 units. In some embodiments, the amount of polyene, when present, can range from about 0.5 mole% to about 4 mole%; about 1.0 mole% to about 3.8 mole%; or about 1.5 mole% to about 2.5 mole%.

Catalyst

[0090] The terms "metallocene" and "metallocene catalyst precursor," as used herein,
30 refer to compounds possessing a transition metal M, with cyclopentadienyl (Cp) ligands, at least one non-cyclopentadienyl-derived ligand X, and zero or one heteroatom-containing ligand Y, the ligands being coordinated to M and corresponding in number to the valence thereof. The metallocene catalyst precursors are generally neutral complexes but when

activated with a suitable co-catalyst yield an active metallocene catalyst, which refers generally to an organometallic complex with a vacant coordination site that can coordinate, insert, and polymerize olefins. The metallocene catalyst precursor is preferably one of, or a mixture of metallocene compounds, of either or both of the following types:


5 (1) cyclopentadienyl (Cp) complexes that have two Cp ring systems for ligands. The Cp ligands form a sandwich complex with the metal and can be free to rotate (unbridged) or locked into a rigid configuration through a bridging group. The Cp ring ligands can be like or unlike unsubstituted, substituted, or a derivative thereof such as a heterocyclic ring system, which may be substituted, and the substitutions can be fused to form other saturated or
 10 unsaturated rings systems such as tetrahydroindenyl, indenyl, or fluorenyl ring systems. These cyclopentadienyl complexes have the general formula:



where Cp^1 of ligand $(\text{Cp}^1\text{R}^1_m)$ and Cp^2 of ligand $(\text{Cp}^2\text{R}^2_p)$ are the same or different cyclopentadienyl rings; R^1 and R^2 each is, independently, a halogen or a hydrocarbyl,
 15 halocarbyl, hydrocarbyl-substituted organometalloid or halocarbyl-substituted organometalloid group containing up to about 20 carbon atoms; m is 0 to 5; p is 0 to 5; and two R^1 and/or R^2 substituents on adjacent carbon atoms of the cyclopentadienyl ring associated there with can be joined together to form a ring containing from 4 to about 20 carbon atoms; R^3 is a bridging group; n is the number of atoms in the direct chain between
 20 the two ligands and is 0 to 8, preferably 0 to 3; M is a transition metal having a valence of from 3 to 6, preferably from group 4, 5, or 6 of the periodic table of the elements and is preferably in its highest oxidation state; each X is a non-cyclopentadienyl ligand and is, independently, a halogen or a hydrocarbyl, oxyhydrocarbyl, halocarbyl, hydrocarbyl-substituted organometalloid, oxyhydrocarbyl-substituted organometalloid or halocarbyl-
 25 substituted organometalloid group containing up to about 20 carbon atoms; q is equal to the valence of M minus 2; and

(2) monocyclopentadienyl complexes that have only one Cp ring system as a ligand. The Cp ligand forms a half-sandwich complex with the metal and can be free to rotate (unbridged) or locked into a rigid configuration through a bridging group to a heteroatom-
 30 containing ligand. The Cp ring ligand can be unsubstituted, substituted, or a derivative thereof such as a heterocyclic ring system which may be substituted, and the substitutions can be fused to form other saturated or unsaturated rings systems, such as tetrahydroindenyl, indenyl, or fluorenyl ring systems. The heteroatom containing ligand is bound to both the

metal and optionally to the Cp ligand through the bridging group. The heteroatom itself is an atom with a coordination number of three from group VA or VIA of the periodic table of the elements. These mono-cyclopentadienyl complexes have the general formula:



5 wherein R^1 is, each independently, a halogen or a hydrocarbyl, halocarbyl, hydrocarbyl-substituted organometalloid or halocarbyl-substituted organometalloid group containing up to about 20 carbon atoms; m is 0 to 5; and two R^1 substituents on adjacent carbon atoms of the cyclopentadienyl ring associated therewith can be joined together to form a ring containing from 4 to about 20 carbon atoms; R^3 is a bridging group; n is 0 to 3; M is a transition metal
 10 having a valence of from 3 to 6, preferably from group 4, 5, or 6 of the periodic table of the elements and is preferably in its highest oxidation state; Y is a heteroatom containing group in which the heteroatom is an element with a coordination number of three from Group VA or a coordination number of two from group VIA preferably nitrogen, phosphorous, oxygen, or sulfur; R^2 is a radical selected from a group consisting of C_1 to C_{20} hydrocarbon radicals,
 15 substituted C_1 to C_{20} hydrocarbon radicals, where one or more hydrogen atoms is replaced with a halogen atom, and when Y is three coordinate and unbridged there may be two R groups on Y each independently a radical selected from a group consisting of C_1 to C_{20} hydrocarbon radicals, substituted C_1 to C_{20} hydrocarbon radicals, where one or more hydrogen atoms is replaced with a halogen atom, and each X is a non-cyclopentadienyl
 20 ligand and is, independently, a halogen or a hydrocarbyl, oxyhydrocarbyl, halocarbyl, hydrocarbyl-substituted organometalloid, oxyhydrocarbyl-substituted organometalloid or halocarbyl-substituted organometalloid group containing up to about 20 carbon atoms; s is equal to the valence of M minus 2.

[0091] Examples of suitable biscyclopentadienyl metallocenes of the type described in
 25 group 1 above can be as discussed and described in U.S. Patent Nos. 5,324,800; 5,198,401; 5,278,119; 5,387,568; 5,120,867; 5,017,714; 4,871,705; 4,542,199; 4,752,597; 5,132,262; 5,391,629; 5,243,001; 5,278,264; 5,296,434; and 5,304,614, which are incorporated by reference herein.

Noncoordinating Anions

30 [0092] The term "noncoordinating anion" (NCA) means an anion that either does not coordinate to the transition metal cation or that is only weakly coordinated to the cation thereby remaining sufficiently labile to be displaced by a neutral Lewis base. "Compatible"

noncoordinating anions are those that are not degraded to neutrality when the initially formed complex decomposes. Further, the anion will not transfer an anionic substituents or fragment to the cation so as to cause it to form a neutral four coordinate metallocene compound and a neutral by-product from the anion. Noncoordinating anions useful in accordance with this invention are those that are compatible, stabilize the metallocene cation in the sense of balancing its ionic charge in a +1 state, and yet retain sufficient lability to permit displacement by an ethylenically or acetylenically unsaturated monomer during polymerization. Additionally, the anions useful in this invention will be large or bulky in the sense of sufficient molecular size to largely inhibit or prevent neutralization of the metallocene cation by Lewis bases other than the polymerizable monomers that may be present in the polymerization process. Typically the anion will have a molecular size of greater than or equal to about 4 angstroms. NCAs are preferred because of their ability to produce a target molecular weight polymer at a higher temperature than tends to be the case with other activation systems such as alumoxane.

[0093] Descriptions of ionic catalysts for coordination polymerization using metallocene cations activated by non-coordinating anions appear in the early work in EP-A-0 277 003; EP-A-0 277 004; WO92/00333; U.S. Patent Nos. 5,198,401 and 5,278,119; which are incorporated by reference herein. These references disclose a preferred method of preparation where metallocenes (bisCp and monoCp) are protonated by an anionic precursors such that an alkyl/hydride group is abstracted from a transition metal to make it both cationic and charge-balanced by the non-coordinating anion. The use of ionizing ionic compounds not containing an active proton but capable of producing both the active metallocene cation and a noncoordinating anion are also known. See, e.g., EP-A-0 426 637, EP-A-0 573 403 and U.S. Patent No. 5,387,568, which are incorporated by reference herein. Reactive cations other than Bronsted acids capable of ionizing the metallocene compounds include ferrocenium triphenylcarbonium and triethylsilylium cations. Any metal or metalloid capable of forming a coordination complex that is resistant to degradation by water (or other Bronsted or Lewis Acids) may be used or contained in the anion of the second activator compound. Suitable metals include, but are not limited to, aluminum, gold, platinum and the like. Suitable metalloids include, but are not limited to, boron, phosphorus, silicon, and the like.

[0094] An additional method for making the ionic catalysts uses ionizing anionic precursors which are initially neutral Lewis acids but form the cation and anion upon ionizing

reaction with the metallocene compounds, for example, tris(pentafluorophenyl) boron acts to abstract an alkyl, hydride or silyl ligand to yield a metallocene cation and stabilizing non-coordinating anion. See, e.g., EP-A-0 427 697 and EP-A-0 520 732, which are incorporated by reference herein. Ionic catalysts for addition polymerization can also be prepared by
5 oxidation of the metal centers of transition metal compounds by anionic precursors containing metallic oxidizing groups along with the anion groups. See, e.g., EP-A-0 495 375, which is incorporated by reference here.

Non-Ionic Activators

[0095] Where the metal ligands include halide moieties, for example, (methyl-phenyl)
10 silylene (tetra-methyl-cyclopentadienyl) (tert-butyl-amido) zirconium dichloride, which are not capable of ionizing abstraction under standard conditions, they can be converted via known alkylation reactions with organometallic compounds such as lithium or aluminum hydrides or alkyls, alkylaluminum compounds, Grignard reagents, etc. See, e.g., EP-A-0 500 944, EP-A1-0 570 982 and EP-A1-0 612 768 for processes describing the reaction of alkyl aluminum
15 compounds with dihalide substituted metallocene compounds prior to or with the addition of activating anionic compounds. For example, an aluminum alkyl compound may be mixed with the metallocene prior to its introduction into the reaction vessel. Since the alkyl aluminum is also suitable as a scavenger its use in excess of that normally stoichiometrically required for alkylation of the metallocene will permit its addition to the reaction solvent with
20 the metallocene compound. Normally, alumoxane would not be added with the metallocene so as to avoid premature activation, but can be added directly to the reaction vessel in the presence of the polymerizable monomers when serving as both scavenger and alkylating activator. Alumoxanes may also fulfill a scavenging function.

[0096] Known alkylaluminum compounds are additionally suitable as catalyst activators,
25 particularly for those metallocenes comprising halide ligands. The alumoxane component useful as catalyst activator typically is an oligomeric aluminum compound represented by the general formula $(R--Al--O)_n$, which is a cyclic compound, or $R(R--Al--O)_nAlR_2$, which is a linear compound. In the general alumoxane formula R is a C_1 to C_5 alkyl radical, for example, methyl, ethyl, propyl, butyl or pentyl, and "n" is an integer from 1 to about 50.
30 Most preferably, R is methyl and "n" is at least 4, i.e., methylalumoxane (MAO). Alumoxanes can be prepared by various procedures known in the art. For example, an aluminum alkyl may be treated with water dissolved in an inert organic solvent, or it may be contacted with a hydrated salt, such as hydrated copper sulfate suspended in an inert organic

solvent, to yield an alumoxane. Generally, however prepared, the reaction of an aluminum alkyl with a limited amount of water yields a mixture of the linear and cyclic species of the alumoxane.

Polymerization Process

5 [0097] Each discrete ethylene-based copolymer can be polymerized in a single, well stirred tank reactor in solution. The viscosity of the solution during polymerization can be less than 10000 cPs, or less than 7000 cPs, and preferably less than 500 cPs. The reactor is preferably a liquid filled, continuous flow, stirred tank reactor providing full back mixing for random copolymer production. Solvent, monomers, and catalyst(s) are fed to the reactor.
10 When two or more reactors are utilized, solvent, monomers, and/or catalyst(s) is fed to the first reactor or to one or more additional reactors.

[0098] Reactors may be cooled by reactor jackets or cooling coils, autorefrigeration, prechilled feeds or combinations of all three to absorb the heat of the exothermic polymerization reaction. Autorefrigerated reactor cooling requires the presence of a vapor
15 phase in the reactor. Adiabatic reactors with prechilled feeds are preferred in which the polymerization exotherm is absorbed by permitting a temperature rise of the polymerizing liquid.

[0099] Use of hydrogen to control molecular weight may be avoided or reduced, if desired. The reactor temperature may be used to control the molecular weight of the polymer
20 fraction produced. In series operation, this gives rise to a temperature difference between reactors, which is helpful for controlling polymer molecular weight.

[00100] Reactor temperature can be selected depending upon the effect of temperature on catalyst deactivation rate and polymer properties and/or extent of monomer depletion. When
25 using more than one reactor, generally temperatures should not exceed the point at which the concentration of catalyst in the second reactor is insufficient to make the desired polymer component in the desired amount. Therefore, reaction temperature can be determined by the details of the catalyst system.

[00101] In general, a single reactor or first reactor in a series will operate at a reactor
30 temperature from about 0°C to about 200°C, or from about 10°C to about 110°C, or from about 20°C to about 90°C. Preferably, reaction temperatures are from about 20°C to about 90°C or from about 20°C to about 70°C. When using on or more additional reactors, the additional reactor temperature will vary from about 40°C to about 200°C, with about 50°C to about 140°C preferred, and about 60°C to about 120°C more preferred. Ranges from any of

the recited lower limits to any of the recited upper limits are contemplated by the inventors and within the scope of the present description. In copolymerization techniques that utilize one or more bis-Cp catalysts with one or more mono-Cp catalysts, a lower reaction temperature is preferred for reactions utilizing mono-Cp catalyst when compared to the bis-Cp catalyst.

[00102] Reaction pressure is determined by the details of the catalyst system. In general a reactor, whether a single reactor or each of a series of reactors, operates at a reactor pressure of less than 2500 pounds per square inch (psi) (17.23 MPa), or less than 2200 psi (15.16 MPa) or less than 2000 psi (13.78 MPa). Preferably, reactor pressure is from about atmospheric pressure to about 2000 psi (13.78 MPa), or from about 200 psi (1.38 MPa) to about 2000 psi (13.78 MPa), or from about 300 psi (2.07 MPa) to about 1800 psi (12.40 MPa). Ranges from any of the recited lower limits to any of the recited upper limits are contemplated and within the scope of the present description.

[00103] In the case of less stable catalysts, catalyst can also be fed to a second reactor when the selected process uses reactors in series. Optimal temperatures can be achieved, particularly for series operation with progressively increasing polymerization temperature, by using bis cyclopentadienyl catalyst systems containing hafnium as the transition metal, especially those having a covalent, single atom bridge coupling the two cyclopentadienyl rings.

[00104] Particular reactor configurations and processes suitable for use in the processes described herein are described in detail in U.S. Patent No. 6,319,998 and U.S. Provisional Patent Application having Serial No. 60/243,192, filed Oct. 25, 2000, which are incorporated by reference herein.

[00105] Branching is introduced by the choice of polymerization catalysts or process. The copolymerization process may occur with or without hydrogen present. However, operation without hydrogen is preferred because it inhibits branching in the copolymers since it lead to chain ends which are completely or substantially saturated. Without being limited by theory, it is believed that these saturated polymers cannot participate in the principal branching pathway where preformed polymers with unsaturated chain ends are reincorporated into new growing chains, which lead to branched polymers.

[00106] In alternative embodiments, the first, second, and third ethylene-based copolymers can be polymerized in an alkane solvent, either hexane in a solution process or propylene in a slurry process and finished to remove the solvent. The first, second, and third ethylene-based

copolymers can have a medium viscosity and a molecular weight in excess of that needed in the final lubricant formulation. For example, most of the traditional EPDM manufacturing plants cannot "finish" low viscosity polymers having the right viscosity for lubricant formulations. In another example, low viscosity copolymers tend to cold flow upon storage.

5 The second example can be particularly true for amorphous copolymers, which have a lower plateau modulus. The bales are then processed by a series of steps to create the final lubricant composition.

[00107] In some embodiments, ethylene and a first comonomer can be polymerized in the presence of a first metallocene catalyst in a first polymerization reaction zone under first

10 polymerization conditions to produce a first effluent comprising a first ethylene-based copolymer. Ethylene and a second comonomer can also be polymerized in the presence of a second metallocene catalyst in a second polymerization reaction zone under second polymerization conditions to produce a second effluent comprising a second ethylene-based copolymer. Ethylene and a third comonomer can also be polymerized in the presence of a

15 third metallocene catalyst in a third polymerization reaction zone under third polymerization conditions to produce a third effluent comprising a third ethylene-based copolymer. The resulting discrete copolymers can then be mixed or otherwise blended to provide the rheology modifier.

[00108] In one or more embodiments, the first and second polymerization conditions can

20 be independently selected from the group consisting of slurry phase, solution phase and bulk phase. When the first and second polymerization conditions are solution phase, forming the polymer blend can further include substantial removal of the solvent from the first effluent, the second effluent, or both to produce a solid polymer blend.

[00109] In one or more embodiments, separate polymerizations can be performed in

25 parallel with the effluent polymer solutions from three reactors combined downstream before the finishing. In another embodiment, separate polymerizations may be performed in series, where the effluent of one reactor is fed to the next reactor. In still another embodiment, the separate polymerization may be performed in the same reactor, preferably in sequential polymerizations.

[00110] The ethylene-based copolymers can be polymerized by a metallocene catalyst to

30 form the first ethylene-based copolymer in one reactor, the second ethylene-based copolymer in another reactor, and the third ethylene-based copolymer in yet another reactor. The first, second, and third ethylene-based copolymers can be combined and then subjected to finishing

steps to produce the polymer blend. The first ethylene-based copolymer can be made first; alternatively, the second or third ethylene-based copolymer can be made first in a series reactor configuration or all three ethylene-based copolymers can be made simultaneously in a parallel reactor configuration.

5 [00111] The metallocene catalysts, and their use with non-coordinating ions and non-ionic activators used in the polymerization process can be as discussed and described in U.S. Provisional Patent Application having Serial No. 61/173,528, entitled "Ethylene-Based Copolymers and Lubricating Oil Compositions Containing the Same," bearing Attorney Docket Number 2009EM079-PRV, filed on April 28, 2009, which is incorporated by
10 reference herein.

[00112] Examples of suitable bis-cyclopentadienyl metallocenes, include, but are not limited to the type disclosed in U. S. Patent Nos. 5,324,800; 5,198,401; 5,278,119; 5,387,568; 5,120,867; 5,017,714; 4,871,705; 4,542,199; 4,752,597; 5,132,262; 5,391,629; 5,243,001; 5,278,264; 5,296,434; and 5,304,614, which are incorporated by reference herein.

15 Lubrication Oil Composition

[00113] Lubricating oil compositions containing the polymer blend and one or more base oils (or basestocks) are also provided. The basestock can be or include natural or synthetic oils of lubricating viscosity, whether derived from hydrocracking, hydrogenation, other refining processes, unrefined processes, or re-refined processes. The basestock can be or
20 include used oil. Natural oils include animal oils, vegetable oils, mineral oils and mixtures thereof. Synthetic oils include hydrocarbon oils, silicon-based oils, and liquid esters of phosphorus-containing acids. Synthetic oils may be produced by Fischer-Tropsch gas-to-liquid synthetic procedure as well as other gas-to-liquid oils.

[00114] In one embodiment, the basestock is or includes a polyalphaolefin (PAO) including a PAO-2, PAO-4, PAO-5, PAO-6, PAO-7 or PAO-8 (the numerical value relating to Kinematic Viscosity at 100°C). Preferably, the polyalphaolefin is prepared from dodecene and/or decene. Generally, the polyalphaolefin suitable as an oil of lubricating viscosity has a viscosity less than that of a PAO-20 or PAO-30 oil. In one or more embodiments, the
25 basestock can be defined as specified in the American Petroleum Institute (API) Base Oil Interchangeability Guidelines. For example, the basestock can be or include an API Group I, II, III, IV, and V oil or mixtures thereof.

[00115] In one or more embodiments, the basestock can include oil or blends thereof conventionally employed as crankcase lubricating oils. For example, suitable basestocks can
30

include crankcase lubricating oils for spark-ignited and compression-ignited internal combustion engines, such as automobile and truck engines, marine and railroad diesel engines, and the like. Suitable basestocks can also include those oils conventionally employed in and/or adapted for use as power transmitting fluids such as automatic transmission fluids, tractor fluids, universal tractor fluids and hydraulic fluids, heavy duty hydraulic fluids, power steering fluids and the like. Suitable basestocks can also be or include gear lubricants, industrial oils, pump oils and other lubricating oils.

[00116] In one or more embodiments, the basestock can include not only hydrocarbon oils derived from petroleum, but also include synthetic lubricating oils such as esters of dibasic acids; complex esters made by esterification of monobasic acids, polyglycols, dibasic acids and alcohols; polyolefin oils, etc. Thus, the lubricating oil compositions described can be suitably incorporated into synthetic base oil basestocks such as alkyl esters of dicarboxylic acids, polyglycols and alcohols; polyalpha-olefins; polybutenes; alkyl benzenes; organic esters of phosphoric acids; polysilicone oils; etc. The lubricating oil composition can also be utilized in a concentrate form, such as from 1 wt% to 49 wt% in oil, e.g., mineral lubricating oil, for ease of handling, and may be prepared in this form by carrying out the reaction of the invention in oil as previously described.

[00117] The lubrication oil composition can include a basestock and one or more compositionally disperse polymer blends and/or one or more crystallinity disperse polymer blends, and optionally, a pour point depressant. The lubrication oil composition can have a thickening efficiency greater than 1.5, or greater than 1.7, or greater than 1.9, or greater than 2.2, or greater than 2.4 or greater than 2.6. The lubrication oil composition can have a shear stability index less than 55, or less than 45, or less than 35, or less than 30, or less than 25, or less than 20, or less than 15. The lubrication oil composition can have a complex viscosity at -35°C of less than 500, or less than 450, or less than 300, or less than 100, or less than 50, or less than 20, or less than 10 centistokes (cSt). The lubrication oil composition can have a Mini Rotary Viscometer (MRV) viscosity at -35°C in a 10W-50 formulation of less than 60,000 cps according to ASTM 1678. The lubrication oil composition can have any combination of desired properties. For example, the lubrication oil composition can have a thickening efficiencies greater than about 1.5 or greater than about 2.6, a shear stability index of less than 55 or less than 35 or less than 25, a complex viscosity at -35°C of less than 500 cSt or less than 300 cSt or less than 50 cSt, and/or a Mini Rotary Viscometer (MRV) viscosity at -35°C in a 10W-50 formulation of less than about 60,000 cps according to ASTM 1678.

[00118] The lubrication oil composition preferably comprises about 2.5 wt%, or about 1.5 wt%, or about 1.0 wt% or about 0.5 wt% of the compositionally disperse and/or crystallinity disperse polymer blend. In some embodiments, the amount of the polymer blend in the lubrication oil composition can range from a low of about 0.5 wt%, about 1 wt%, or about 2 wt% to a high of about 2.5 wt%, about 3 wt%, about 5 wt%, or about 10 wt%.

Oil Additives

[00119] The lubricating oil compositions of the invention can optionally contain one or more conventional additives, such as, for example, pour point depressants, antiwear agents, antioxidants, other viscosity-index improvers, dispersants, corrosion inhibitors, anti-foaming agents, detergents, rust inhibitors, friction modifiers, and the like.

[00120] Corrosion inhibitors, also known as anti-corrosive agents, reduce the degradation of the metallic parts contacted by the lubricating oil composition. Illustrative corrosion inhibitors include phosphosulfurized hydrocarbons and the products obtained by reaction of a phosphosulfurized hydrocarbon with an alkaline earth metal oxide or hydroxide, preferably in the presence of an alkylated phenol or of an alkylphenol thioester, and also preferably in the presence of carbon dioxide. Phosphosulfurized hydrocarbons are prepared by reacting a suitable hydrocarbon such as a terpene, a heavy petroleum fraction of a C₂ to C₆ olefin polymer such as polyisobutylene, with from 5 to 30 wt% of a sulfide of phosphorus for 1/2 to 15 hours, at a temperature in the range of 66°C to 316°C. Neutralization of the phosphosulfurized hydrocarbon may be effected in the manner known by those skilled in the art.

[00121] Oxidation inhibitors, or antioxidants, reduce the tendency of mineral oils to deteriorate in service, as evidenced by the products of oxidation such as sludge and varnish-like deposits on the metal surfaces, and by viscosity growth. Such oxidation inhibitors include alkaline earth metal salts of alkylphenolthioesters having C₅ to C₁₂ alkyl side chains, e.g., calcium nonylphenate sulfide, barium octylphenate sulfide, dioctylphenylamine, phenylalphanaphthylamine, phosphosulfurized or sulfurized hydrocarbons, etc. Other oxidation inhibitors or antioxidants useful in this invention include oil-soluble copper compounds, such as described in U.S. Patent No. 5,068,047.

[00122] Friction modifiers serve to impart the proper friction characteristics to lubricating oil compositions such as automatic transmission fluids. Representative examples of suitable friction modifiers are found in U.S. Patent No. 3,933,659, which discloses fatty acid esters and amides; U.S. Patent No. 4,176,074 which describes molybdenum complexes of

polyisobutenyl succinic anhydride-amino alkanols; U.S. Patent No. 4,105,571 which discloses glycerol esters of dimerized fatty acids; U.S. Patent No. 3,779,928 which discloses alkane phosphonic acid salts; U.S. Patent No. 3,778,375 which discloses reaction products of a phosphonate with an oleamide; U.S. Patent No. 3,852,205 which discloses S-carboxyalkylene hydrocarbyl succinimide, S-carboxyalkylene hydrocarbyl succinamic acid and mixtures thereof; U.S. Patent No. 3,879,306 which discloses N(hydroxyalkyl)alkenyl-succinamic acids or succinimides; U.S. Patent No. 3,932,290 which discloses reaction products of di-(lower alkyl) phosphites and epoxides; and U.S. Patent No. 4,028,258 which discloses the alkylene oxide adduct of phosphosulfurized N-(hydroxyalkyl) alkenyl succinimides. Preferred friction modifiers are succinate esters, or metal salts thereof, of hydrocarbyl substituted succinic acids or anhydrides and thiobis-alkanols, such as described in U.S. Patent No. 4,344,853.

[00123] Dispersants maintain oil insolubles, resulting from oxidation during use, in suspension in the fluid, thus preventing sludge flocculation and precipitation or deposition on metal parts. Suitable dispersants include high molecular weight N-substituted alkenyl succinimides, the reaction product of oil-soluble polyisobutylene succinic anhydride with ethylene amines such as tetraethylene pentamine and borated salts thereof. High molecular weight esters (resulting from the esterification of olefin substituted succinic acids with mono or polyhydric aliphatic alcohols) or Mannich bases from high molecular weight alkylated phenols (resulting from the condensation of a high molecular weight alkylsubstituted phenol, an alkylene polyamine and an aldehyde such as formaldehyde) are also useful as dispersants.

[00124] Pour point depressants ("ppd"), otherwise known as lube oil flow improvers, lower the temperature at which the fluid will flow or can be poured. Any suitable pour point depressant known in the art can be used. For example, suitable pour point depressants include, but are not limited to, one or more C₈ to C₁₈ dialkylfumarate vinyl acetate copolymers, polymethyl methacrylates, alkylmethacrylates and wax naphthalene.

[00125] Foam control can be provided by any one or more anti-foamants. Suitable anti-foamants include polysiloxanes, such as silicone oils and polydimethyl siloxane.

[00126] Anti-wear agents reduce wear of metal parts. Representatives of conventional antiwear agents are zinc dialkyldithiophosphate and zinc diaryldithiophosphate, which also serves as an antioxidant.

[00127] Detergents and metal rust inhibitors include the metal salts of sulphonic acids, alkyl phenols, sulfurized alkyl phenols, alkyl salicylates, naphthenates and other oil soluble

mono- and dicarboxylic acids. Highly basic (viz, overbased) metal sales, such as highly basic alkaline earth metal sulfonates (especially Ca and Mg salts) are frequently used as detergents.

[00128] Compositions containing these conventional additives can be blended with the basestock in amounts effective to provide their normal attendant function. Thus, typical formulations can include, in amounts by weight, a VI improver (from about 0.01% to about 12%); a corrosion inhibitor (from about 0.01% to about 5%); an oxidation inhibitor (from about 0.01% to about 5%); depressant (of from about 0.01% to about 5%); an anti-foaming agent (from about 0.001% to about 3%); an anti-wear agent (from about 0.001% to about 5%); a friction modifier (from about 0.01% to about 5%); a detergent/rust inhibitor (from about 0.01 to about 10%); and a base oil.

[00129] When other additives are used, it may be desirable, although not necessary, to prepare additive concentrates that include concentrated solutions or dispersions of the VI improver (in concentrated amounts), together with one or more of the other additives, such a concentrate denoted an "additive package," whereby several additives can be added simultaneously to the basestock to form a lubrication oil composition. Dissolution of the additive concentrate into the lubrication oil can be facilitated by solvents and by mixing accompanied with mild heating, but this is not essential. The additive-package can be formulated to contain the VI improver and optional additional additives in proper amounts to provide the desired concentration in the final formulation when the additive-package is combined with a predetermined amount of base oil.

Blending With Basestock Oils

[00130] Conventional blending methods are described in U.S. Patent No. 4,464,493, which is incorporated by reference herein. This conventional process requires passing the polymer through an extruder at elevated temperature for degradation of the polymer and circulating hot oil across the die face of the extruder while reducing the degraded polymer to particle size upon issuance from the extruder and into the hot oil. The pelletized, solid polymer compositions of the present invention, as described above, can be added by blending directly with the base oil so as give directly viscosity for the VI improver, so that the complex multi-step process of the prior art is not needed. The solid polymer composition can be dissolved in the basestock without the need for additional shearing and degradation processes.

[00131] The polymer compositions will be soluble at room temperature in lube oils at up to 10 percent concentration in order to prepare a viscosity modifier concentrate. Such concentrates, including eventually an additional additive package including the typical

additives used in lube oil applications as described above, are generally further diluted to the final concentration (usually around 1%) by multi-grade lube oil producers. In this case, the concentrate will be a pourable homogeneous solid free solution.

5 [00132] The polymer blend compositions preferably have an SSI (determined according to ASTM D97) of from about 10 to about 50.

Specific Embodiments

10 [00133] In one or more specific embodiments, the present invention is directed to a polymer blend composition for use as a VI improver comprising a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer. The first copolymer has an ethylene content from about 35 to about 55 wt%, or from about 40 to about 55 wt%, or from about 45 to about 53 wt%; the second copolymer has an ethylene content from about 55 to about 85 wt%, or from about 55 to about 73 wt%, or from about 65 to about 73 wt%; and the third copolymer has an ethylene content from about 65 to about 85 wt%, or from about 70 to about 85 wt%, or from about 71 to about 85 wt%. Additionally, the ethylene content of the second copolymer is at least about 15 wt%, or at least about 18 wt%, or at least about 22 wt% greater than that ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 5 wt%, or at least about 6 wt%, or at least about 8 wt% greater than the ethylene content of the second copolymer.

20 [00134] In the same or other embodiments, the first copolymer has a first melt heat of fusion from about 0 to about 30 J/g, or from about 0 to about 15 J/g, or from about 0 to about 10 J/g; the second copolymer has a first melt heat of fusion from about 30 to about 50 J/g, or from about 35 to about 48 J/g, or from about 40 to about 48 J/g; and the third copolymer has a first melt heat of fusion from about 40 to about 85 J/g, or from about 55 to about 75 J/g, or from about 65 to about 75 J/g. Additionally, the heat of fusion of the third copolymer is at least about 5 J/g, or at least about 8 J/g, or at least about 12 J/g greater than that ethylene content of the second copolymer.

25 [00135] Further, the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000. In the same or other embodiments, the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0. Additionally, the composition comprises from about 15 to about 85 wt%, or from about 25 to about 75 wt%, or from about

30

35 to about 65 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

[00136] The first, second, and third copolymers of the invention may each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

5 [00137] Further embodiments of the present invention include lubricating oil compositions comprising a lubricating oil basestock and any of the polymer blend compositions of the invention described herein.

Polymer Analyses

[00138] The ethylene contents as an ethylene weight percent (C₂ wt%) for the ethylene-
10 based copolymers were determined according to ASTM D1903.

[00139] DSC Measurements of the crystallization temperature, T_c, and melting temperature, T_m, of the ethylene-based copolymers were measured using a TA Instruments Model 2910 DSC. Typically, 6-10 mg of a polymer was sealed in a pan with a hermetic lid and loaded into the instrument. In a nitrogen environment, the sample was first cooled to -
15 100°C at 20°C/min. It was then heated to 220°C at 10°C/min and melting data (first heat) were acquired. This provides information on the melting behavior under as-received conditions, which can be influenced by thermal history as well as sample preparation method. The sample was then equilibrated at 220°C to erase its thermal history. Crystallization data (first cool) were acquired by cooling the sample from the melt to -100°C at 10°C/min and
20 equilibrated at -100°C. Finally the sample was heated again to 220°C at 10°C/min to acquire additional melting data (second heat). The endothermic melting transition (first and second heat) and exothermic crystallization transition (first cool) were analyzed for peak temperature and area under the peak. The term "melting point," as used herein, is the highest peak among principal and secondary melting peaks as determined by DSC during the second melt, discussed above. The thermal output was recorded as the area under the melting peak of the
25 sample, which was typically at a maximum peak at about 30°C to about 175°C and occurred between the temperatures of about 0°C and about 200°C. The thermal output was measured in Joules as a measure of the heat of fusion. The melting point is recorded as the temperature of the greatest heat absorption within the range of melting of the sample.

30 [00140] Molecular weight (weight-average molecular weight, M_w, number-average molecular weight, M_n, and molecular weight distribution, M_w/M_n or MWD) were determined using a High Temperature Size Exclusion Chromatograph (either from Waters Corporation or Polymer Laboratories), equipped with a differential refractive index detector

(DRI), an online light scattering (LS) detector, and a viscometer. Experimental details not described below, including how the detectors were calibrated, are described in: T. Sun, P. Brant, R. R. Chance, and W. W. Graessley, *MACROMOLECULES*, Vol. 34, Number 19, pp. 6812-6820, (2001).

5 [00141] Three Polymer Laboratories PLgel 10mm Mixed-B columns were used. The nominal flow rate was 0.5 cm³/min, and the nominal injection volume was 300 μL. The various transfer lines, columns and differential refractometer (the DRI detector) were contained in an oven maintained at 145°C. Solvent for the SEC experiment was prepared by dissolving 6 grams of butylated hydroxy toluene as an antioxidant in 4 liters of Aldrich
10 reagent grade 1, 2, 4 trichlorobenzene (TCB). The TCB mixture was then filtered through a 0.7 μm glass pre-filter and subsequently through a 0.1 μm Teflon filter. The TCB was then degassed with an online degasser before entering the SEC. Polymer solutions were prepared by placing dry polymer in a glass container, adding the desired amount of TCB, then heating the mixture at 160°C with continuous agitation for about 2 hours. All quantities were
15 measured gravimetrically. The TCB densities used to express the polymer concentration in mass/volume units are 1.463 g/ml at room temperature and 1.324 g/ml at 145°C. The injection concentration ranged from about 1.0 mg/ml to about 2.0 mg/ml, with lower concentrations being used for higher molecular weight samples. Prior to running each sample the DRI detector and the injector were purged. Flow rate in the apparatus was then increased
20 to 0.5 ml/minute, and the DRI was allowed to stabilize for about 8 to 9 hours before injecting the first sample. The LS laser was turned on from about 1 hour to about 1.5 hours before running samples.

[00142] The concentration, *c*, at each point in the chromatogram is calculated from the baseline-subtracted DRI signal, *I*_{DRI}, using the following equation:

25
$$c = K_{\text{DRI}} I_{\text{DRI}} / (dn/dc)$$

where *K*_{DRI} is a constant determined by calibrating the DRI, and (dn/dc) is the same as described below for the light scattering (LS) analysis. Units on parameters throughout this description of the SEC method are such that concentration is expressed in g/cm³, molecular weight is expressed in g/mole, and intrinsic viscosity is expressed in dL/g.

30 [00143] The light scattering detector used was a Wyatt Technology High Temperature mini-DAWN. The polymer molecular weight, *M*, at each point in the chromatogram is determined by analyzing the LS output using the Zimm model for static light scattering (M.B. Huglin, *LIGHT SCATTERING FROM POLYMER SOLUTIONS*, Academic Press, 1971):

$$\frac{K_o c}{\Delta R(\theta)} = \frac{1}{MP(\theta)} + 2A_2 c$$

Here, $\Delta R(\theta)$ is the measured excess Rayleigh scattering intensity at scattering angle θ , c is the polymer concentration determined from the DRI analysis, A_2 is the second virial coefficient [for purposes of this invention and the claims thereto, $A_2 = 0.0006$ for propylene polymers and 0.001 otherwise], $P(\theta)$ is the form factor for a monodisperse random coil (M.B. Huglin, LIGHT SCATTERING FROM POLYMER SOLUTIONS, Academic Press, 1971), and K_o is the optical constant for the system:

$$K_o = \frac{4\pi^2 n^2 (dn/dc)^2}{\lambda^4 N_A}$$

in which N_A is Avogadro's number, and (dn/dc) is the refractive index increment for the system. The refractive index, $n = 1.500$ for TCB at 145°C and $\lambda = 690$ nm. For purposes of this invention and the claims thereto $(dn/dc) = 0.104$ for propylene polymers and 0.1 otherwise.

[00144] A high temperature Viscotek Corporation viscometer, which has four capillaries arranged in a Wheatstone bridge configuration with two pressure transducers, was used to determine specific viscosity. One transducer measures the total pressure drop across the detector, and the other, positioned between the two sides of the bridge, measures a differential pressure. The specific viscosity, η_s , for the solution flowing through the viscometer is calculated from their outputs. The intrinsic viscosity, $[\eta]$, at each point in the chromatogram is calculated from the following equation:

$$\eta_s = c[\eta] + 0.3(c[\eta])^2$$

where c is concentration and was determined from the DRI output.

[00145] The branching index (g') is calculated using the output of the SEC-DRI-LS-VIS method as follows. The average intrinsic viscosity, $[\eta]_{\text{avg}}$, of the sample is calculated by:

$$[\eta]_{\text{avg}} = \frac{\sum c_i [\eta]_i}{\sum c_i}$$

where the summations are over the chromatographic slices, i , between the integration limits.

[00146] The branching index g' is defined as:

$$g' = \frac{[\eta]_{\text{avg}}}{kM_v^\alpha}$$

where, for purpose of this invention and claims thereto, $\alpha = 0.695$ for ethylene, propylene, and butene polymers; and $k = 0.000579$ for ethylene polymers, $k = 0.000228$ for propylene polymers, and $k = 0.000181$ for butene polymers. M_v is the viscosity-average molecular weight based on molecular weights determined by LS analysis.

5 [00147] Anton-Parr Low Temperature Solution Rheology (low temperature rheology) experiments were done on an Anton-Parr Model MCR501 rheometer using a 1" cone and plate setup. The cone has a nominal 1 degree angle and 50 micron gap. About 100 microliters of sample is deposited on the bottom plate using a syringe-pipette. The cone is then lowered onto the plate so that the volume between the cone and plate is fully occupied
10 by solution. The temperature is then lowered at a cooling rate of 1.5°C/min. while measuring the complex viscosity at an angular frequency of 0.1 radians/sec. applying a 10% strain and recording a value every minute. The viscosity at 0.1 rad/sec is then plotted as a function of temperature to observe the effect of gelation.

Scanning Brookfield Viscometer

15 [00148] The Scanning Brookfield Viscometer was operated according to ASTM D5133. 25 ml to 30 ml of the sample was poured into a glass stator to the fill line, which was immersed into an oil bath. The oil bath was programmed to cool from -5°C to -40°C at 1°C/hour scanning speed. The sample was preheated to 90°C for 90 minutes to remove thermal history. The temperature ramping program was set to cool from -5°C to -40°C at
20 1°C/hour scanning speed. In sample collection mode, the Gelation Index (GI) and maximum viscosity can be viewed. The torque versus temperature data set can be converted to a viscosity-temperature plot at which a gelation point and/or corresponding gelation index can be established.

[00149] Melt Index (MI) was measured according to ASTM D1238 at 190°C under a 2.16
25 kilogram load.

[00150] Melt Flow Rate (MFR) was measured according to ASTM D1238 at 230°C under a 2.16 kilogram load or a 21.6 kilogram load.

[00151] Thickening Efficiency (TE) was determined according to ASTM D445.

[00152] Shear Stability index (SSI) was determined according to ASTM D6278 at 30 and
30 90 cycles using a Kurt Orbahn machine.

[00153] Shear stress data was accomplished by first heating the sample to -15°C, and waiting for 15 minutes. Then while measuring the shear stress, applying a logarithmically

increasing strain by varying the shear rate logarithmically from 10^{-3} to 10 with 20 points/decade and 1 second per point.

[00154] The number of branch points was determined by measuring the radius of gyration of polymers as a function of the molecular weight by the methods of size exclusion chromatography augmented by laser light scattering. These procedures are described in the publications "A Study of the Separation Principle in Size Exclusion Chromatography" by T. Sun, R. R. Chance, W. W. Graessley and D. J. Lohse in the journal *MACROMOLECULES*, 2004, Vol. 37, Issue 11, pp. 4304–4312, and "Effect of Short Chain Branching on the Coil Dimensions of Polyolefins in Dilute Solution" by T. Sun, R. R. Chance, W. W. Graessley and P. Brant in the journal *MACROMOLECULES*, 2001, Vol. 34, Issue 19, pp. 6812–6820, which are incorporated by reference herein.

[00155] Branching in polymers having narrow, and most probably, low polydispersity index with essentially uniform intramolecular and intermolecular distribution of composition can also be described by the ratio of the TE to the MFR@230°C measured at a load of 2.16Kg. High values of this parameter indicate low levels of branching while low levels indicate substantial levels of branching.

[00156] Intermolecular composition distribution, unlike CDBI, contemplates weight percent of copolymer content within a smaller range from a median total molar comonomer content, e.g., within 25 wt% of median. For example, for a Gaussian compositional distribution, 95.5% of the polymer, used herein for this example as "Polymer Fraction", is within 20 wt% ethylene of the mean if the standard deviation is 10%. The intermolecular composition distribution for the Polymer Fraction is 20 wt% ethylene for such a sample, i.e., 10% standard deviation yields 20 wt% intermolecular composition distribution.

[00157] Compositional Heterogeneity, both intermolecular-CD and intramolecular-CD can be determined by carbon-13 NMR. Conventional techniques for measuring intermolecular-CD and intramolecular-CD are described in *MACROMOLECULES*, H. N. Cheng, Masahiro Kakugo, entitled "Carbon-13 NMR analysis of compositional heterogeneity in ethylene-propylene copolymers," Vol. 24, Issue 8, pp. 1724–1726, (1991), and in the publication *MACROMOLECULES*, C. Cozewith, entitled "Interpretation of carbon-13 NMR sequence distribution for ethylene-propylene copolymers made with heterogeneous catalysts," Vol. 20, Issue 6, pp. 1237–1244, (1987).

[00158] Generally, conventional carbon-13 NMR measurements of diad and triad distribution is used to characterize the ethylene-based copolymer. Any conventional

technique for measuring carbon-13 NMR may be utilized. For example, ethylene-based copolymer samples are dissolved in a solvent, e.g., trichlorobenzene at 4.5 wt% concentration. The carbon-13 NMR spectra are obtained at elevated temperature, e.g., 140°C, on a NMR spectrometer at 100 MHz. An exemplary spectrometer is a pulsed Fourier transform Varian XL-400 NMR spectrometer. Deuteriated o-dichlorobenzene is placed in a coaxial tube to maintain an internal lock signal. The following instrument conditions are utilized: pulse angle, 75°; pulse delay, 25 second; acquisition time, 0.5 second, sweep width, 16000 Hz. The carbon-13 NMR peak area measurements were determined by spectral integration. Diad and triad concentrations were calculated from the equations presented in MACROMOLECULES, Kakugo *et al.*, Vol. 15, Issue 4, pp. 1150-1152, (1982). The diad and triad concentrations were then normalized to give a mole fraction distribution. Polymer composition was calculated from the methane peaks, the methylene peaks, and the diad balance. These values may be considered individually or an average of the three values may be utilized. Unless stated otherwise, this application utilizes an average of these three values. The results are then compared to conventional model equations as disclosed in the above references.

[00159] One aspect of these measurements involves the determination of the reactivity ratios ($r_1 r_2$) of the polymerization system for the ethylene-based polymers according to the procedures in the publication. Polymers that have a compositional heterogeneity, either intramolecular or intermolecular, have a much larger reactivity ratio than the polymers that have only a small or negligible amount.

[00160] Without being limited to theory or one method of calculation, it is believed that an one exemplary model for, so called ideal copolymerizations, is described by the terminal copolymerization model:

$$m = M(r_1 M + I)/(r_2 + M) \quad (1)$$

wherein r_1 and r_2 are the reactivity ratios, m is the ratio of monomers in the copolymer, m_1/m_2 , M is the ratio of monomers in the reactor, M_1/M_2 , and the diad and triad concentrations follow first order Markov statistics. For this model, nine equations are derived that related to the diad and triad concentrations P_{12} and P_{21} , the probability of propylene adding to an ethylene-ended chain, and the probability of propylene adding to a propylene-ended chain, respectively. Thus a fit of carbon-13 NMR data to these equations

yields P_{12} and P_{21} as the model parameters from which r_1 and r_2 can be obtained from the relationships:

$$r_1 M = (1 - P_{12}) / P_{12}$$

$$r_2 / M = (1 - P_{21}) / P_{21}$$

5

[00161] The corresponding equations for random copolymerizations with $r_1 r_2 = 1$ can also be used to simplify equation (1), above, to $m = r_1 M$. The ethylene fraction in the polymer, E , is equal to $1 - P_{12}$. This allows the diad and triad equations to be written in terms of polymer composition:

10

$$EE = E^2$$

$$EE = 2E(1 - E)$$

$$PP = (1 - E)^2$$

$$EEE = E^3$$

$$EEP = 2E^2(1 - E)$$

15

$$EPE = E^2(1 - E)$$

$$PEP = E(1 - E)^2$$

$$PPE = 2E(1 - E)^2$$

$$PPP = (1 - E)^3$$

20

[00162] Variations and extensions of these equations are provided in the references incorporated herein, including use of catalysts with different active sites, equations for estimating the number of catalyst species present, or complex models such as those with three or more species present, etc.

25

[00163] From these modeling equations, and those equations presented by MACROMOLECULES, C. Cozewith, Ver Strate, Vol. 4, pp. 482-489, (1971), the average values of \bar{r}_1 , \bar{r}_2 , and $\overline{r_1 r_2}$ arising from the copolymerization kinetics are given by:

$$\bar{r}_1 = (\sum r_{1j} f_j / G_i) / (\sum f_j / G_i)$$

$$\bar{r}_2 = (\sum r_{2j} f_j / G_i) / (\sum f_j / G_i)$$

$$\overline{r_1 r_2} = (\sum r_{1j} f_j / G_i) (\sum r_{2j} f_j / G_i) / (\sum f_j / G_i)^2$$

30

$$\text{where } G_i = r_{1i} M \pm 2 + \underline{r_{2i}} / M$$

These equations and the models presented in the references cited above may be utilized by those skilled in the art to characterize the ethylene-based copolymer composition distribution.

[00164] Further information and techniques for measuring intramolecular-CD are found in MACROMOLECULES, Randel, James C., Vol. 11, Issue 1, pp. 33-36, (1978),
5 MACROMOLECULES, Cheng, H.N., Vol. 17, Issue 10, pp. 1950-1955, (1984), and
MACROMOLECULES, Ray, G. Joseph, Johnson, Paul E., and Knox, Jack R., Vol. 10 Issue 4,
pp. 773-778, (1977), which are incorporated by reference herein. Such techniques are readily
known to those skilled in the art of analyzing and characterizing olefin polymers.

[00165] Temperature Rising Elution Fractionation (TREF). The determination of
10 intermolecular compositional heterogeneity was determined by the fractionation of the EP
copolymer carried out by a Polymer Char TREF 200 based on a well-known principle that the
solubility of a semi-crystalline copolymer is a strong function of temperature. A
corresponding method is described in U.S. Patent No. 5,008,204. The instrument is a column
packed with solid stainless-steel beads. The copolymer of interest was dissolved in 1,2 ortho-
15 dichlorobenzene (oDCB) at 160°C for 60 min. Half of a milliliter (ml) of the polymer
solution (concentration = 4-5 mg/ml) was injected in the column and it was stabilized there at
140°C for 45 min. The solution was cooled from 140°C to -15°C at 1°C/min and equilibrated
at this temperature for 10 min. This caused the copolymer to crystallize out of the quiescent
solution in successive layers of decreasing crystallinity onto the surface of the beads. Pure
20 solvent (oDCB) was pumped for 5 min at -15°C at a flow rate of 1 ml/min through an
infrared detector. A valve was then switched to allow this chilled oDCB to flow through the
column at the same flow rate at -15°C for 10 min. The material eluted was designated as the
soluble fraction of the copolymer. At this point, the heater was on and the solvent continued
to flow through both the column and the infrared detector while the temperature was
25 programmed upward at a controlled rate of 2°C/min to 140°C. The infrared detector
continuously measured the concentration of the copolymer in the effluent from the column,
and a continuous solubility distribution curve was obtained.

[00166] Described below are further embodiments of the inventions provided herein:

A. A polymer blend composition comprising a first ethylene-based copolymer, a second
30 ethylene-based copolymer, and a third ethylene-based copolymer, wherein the first
copolymer has an ethylene content from about 35 to about 55 wt%; the second copolymer has
an ethylene content from about 55 to about 85 wt%; the third copolymer has an ethylene
content from about 65 to about 85 wt%; the ethylene content of the second copolymer is at

least about 15 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 5 wt% greater than the ethylene content of the second copolymer; the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000; the ratio of the melt index of the first
5 copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

10 B. The polymer blend composition of paragraph A, wherein the first copolymer has an ethylene content from about 40 to about 55 wt%, the second copolymer has an ethylene content from about 55 to about 73 wt%, and the third copolymer has an ethylene content from about 70 to about 85 wt%.

15 C. The polymer blend composition of any of paragraphs A and B, wherein the first copolymer has an ethylene content from about 45 to about 53 wt%, the second copolymer has an ethylene content from about 65 to about 73 wt%, and the third copolymer has an ethylene content from about 71 to about 85 wt%.

20 D. The polymer blend composition of any of paragraphs A through C, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

E. The polymer blend composition of any of paragraphs A through D, wherein the ethylene content of the second copolymer is at least about 18 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

25 F. The polymer blend composition of any of paragraphs A through E, wherein the ethylene content of the second copolymer is at least about 22 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 8 wt% greater than the ethylene content of the second copolymer.

30 G. The polymer blend composition of any of paragraphs A through F, wherein the composition comprises from about 25 to about 75 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

H. The polymer blend composition of claim 7 any of paragraphs A through G, wherein the composition comprises from about 35 to about 65 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

I. A polymer blend composition comprising a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, wherein the first copolymer has a first melt heat of fusion from about 0 to about 30 J/g; the second copolymer has a first melt heat of fusion from about 30 to about 50 J/g; the third copolymer has a first melt heat of fusion from about 40 to about 85 J/g; the heat of fusion of the third copolymer is at least about 5 J/g greater than the heat of fusion of the second copolymer; the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000; the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

J. The polymer blend composition of any of paragraphs A through I, wherein the first copolymer has a first melt heat of fusion from about 0 to about 15 J/g, the second copolymer has a first melt heat of fusion from about 35 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 55 to about 75 J/g.

K. The polymer blend composition of any of paragraphs A through J, wherein the first copolymer has a first melt heat of fusion from about 0 to about 10 J/g, the second copolymer has a first melt heat of fusion from about 40 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 65 to about 75 J/g.

L. The polymer blend composition of any of paragraphs A through K, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

M. The polymer blend composition of any of paragraphs A through L, wherein the heat of fusion of the third copolymer is at least about 8 J/g greater than the heat of fusion of the second copolymer.

N. The polymer blend composition of any of paragraphs A through M, wherein the heat of fusion of the third copolymer is at least about 12 J/g greater than the heat of fusion of the second copolymer.

O. The polymer blend composition of any of paragraphs A through N, wherein the composition comprises from about 25 to about 75 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

P. The polymer blend composition of any of paragraphs A through O, wherein the composition comprises from about 35 to about 65 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

Q. A lubricating oil composition comprising a lubricating oil basestock, a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer wherein the first copolymer has an ethylene content from about 35 to about 55 wt%; the second copolymer has an ethylene content from about 55 to about 85 wt%; the third copolymer has an ethylene content from about 65 to about 85 wt%; the ethylene content of the third copolymer is at least about 5 wt% greater than the ethylene content of the second copolymer; the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000; the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

R. The lubricating oil composition of paragraph Q, wherein the first copolymer has an ethylene content from about 45 to about 53 wt%, the second copolymer has an ethylene content from about 65 to about 73 wt%, and the third copolymer has an ethylene content from about 71 to about 85 wt%.

S. The lubricating oil composition of any of paragraphs Q or R, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

T. The lubricating oil composition of any of paragraphs Q through S, wherein the ethylene content of the second copolymer is at least about 18 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

U. A lubricating oil composition comprising a lubricating oil basestock, a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, wherein the first copolymer has a first melt heat of fusion from about 0 to about 30 J/g; the second copolymer has a first melt heat of fusion from about 30 to about 50 J/g; the third

copolymer has a first melt heat of fusion from about 40 to about 85 J/g; the heat of fusion of the third copolymer is at least about 5 J/g greater than the heat of fusion of the second copolymer; the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000; the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

V. The lubricating oil composition of any of paragraphs Q through U, wherein the first copolymer has a first melt heat of fusion from about 0 to about 10 J/g, the second copolymer has a first melt heat of fusion from about 40 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 65 to about 75 J/g.

W. The lubricating oil composition of any of paragraphs Q through V, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

X. The lubricating oil composition of any of paragraphs Q through W, wherein the ethylene content of the second copolymer is at least about 18 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

Y. A method for making a polymer blend or lubricating oil composition of any of embodiments A-X comprising combining the first copolymer, the second copolymer and third copolymer recited therein, and forming the composition.

EXAMPLES

Preparation of the Ethylene-Based Copolymers

[00167] A variety of ethylene-based copolymers as described above were synthesized as follows. Ethylene and propylene were polymerized in solution in a continuous stirred tank reactor, using hexane as a solvent. Polymerization in the reactor was performed at a temperature of about 110-115°C, an overall pressure of about 20 bar, and ethylene and propylene feed rates of about 1.3 and 2.0 kg/hr, respectively. N,N-dimethylanilinium tetrakis(pentafluorophenyl) boron was used to activate di(p-triethylsilylphenyl) methenyl[(cyclopentadienyl)(2,7-di-tert-butylfluorophenyl)]hafnium dimethyl as the catalyst. During the polymerization process, hydrogen addition and temperature control were used to

achieve the desired melt flow rate. The catalyst, activated externally to the reactor, was added as needed in amounts effective to maintain the target polymerization temperature.

[00168] The copolymer solution exiting the reactor was stopped from further polymerization by the addition of water and then devolatilized using conventional techniques such as, for example, flashing or liquid phase separation, first by removing the bulk of the hexane to provide a concentrated solution, then by stripping the remainder of the solvent in anhydrous conditions using a devolatilizer or a twin screw devolatilizing extruder so as to result in a molten polymer composition comprising less than 0.5 wt% solvent and other volatiles. The molten polymer was cooled until solid.

[00169] The compositions and other properties of the polymers thus prepared are set forth in Table 1. Polymers that meet the description of the first ethylene-based copolymer as described above are designated “EA,” polymers that meet the description of the second ethylene-based copolymer as described above are designated “EB,” and polymers that meet the description of the third ethylene-based polymer are designated “EC.”

Table 1

	EA1	EA2	EB1	EB2	EC1	EC2	EC3
Mw, g/mol	92958	96720	74883	77890	65983	94434	80194
Mw/Mn	2.25	2.20	2.28	2.24	2.23	2.23	2.18
C ₂ , wt%	48.98	45.65	70.41	66.82	72.57	76.42	79.28
MFR, g/10 min (2.16 kg, 230°C)	5.53	5.97	6.40	4.99	8.32	1.49	2.64
T _m , °C (1 st melt)	-35.0	n/a	43.6	15.0	44.8	48.6	55.5
H _f , J/g (1 st melt)	0.4	n/a	45.0	44.0	58.5	70.4	73.6
T _c , °C (2 nd cool)	-50.6	n/a	14.6	11.6	18.5	37.9	44.6
H _c , J/g (2 nd cool)	2.4	n/a	46.4	36.2	52.1	61.4	59.6
T _m , °C (2 nd melt)	-36.4	n/a	19.2	11.0	30.2	48.5	53.8
H _f , J/g (2 nd melt)	0.6	n/a	46.5	43.3	51.2	63.5	67.9
T _g , °C	-58.6	-57.5	-48.1	-48.1	-45.0	-40.3	-40.3

Examples 1-50

[00170] Polymer blend compositions were prepared comprising a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, all of which were selected from the polymers listed in Table 1. The blends were made by melt blending in a Brabender mixer having an internal cavity of 250 ml at a temperature of from about 120 to about 150°C for 3 to 5 minutes using low shear blades rotating at a speed of 15 to 20 rpm. The ethylene-based copolymers were protected during the mixing operation with

a nitrogen blanket and by the addition of 1000 ppm of a 3:1 mixture of Irganox 1076 and Irgafos 168 (both available from BASF Corporation) before blending. The compositions of the resulting polymer blends are set forth in Table 2 below, and the amounts of each component are given in grams.

5

Table 2

Example No.	EA2	EA1	EB1	EC1	EC2	EB2	EC3
1	240		120	40			
2	200		120	80			
3	160		120	120			
4	120		120	160			
5	80		120	200			
6	240		120		40		
7	200		120		80		
8	160		120		120		
9	120		120		160		
10	80		120		200		
11	160		200	40			
12	120		200	80			
13	80		200	120			
14	160		200		40		
15	120		200		80		
16	80		200		120		
17		280	80				40
18		280				80	40
19		280	40				80
20		280				40	80
21		240	120				40
22		240				120	40
23		240	80				80
24		240				80	80
25		240	40				120
26		240				40	120
27		200	160				40
28		200				160	40
29		200	120				80
30		200				120	80

Table 2 Cont.

Example No.	EA2	EA1	EB1	EC1	EC2	EB2	EC3
31		200	80				120
32		200				80	120
33		200	40				160
34		200				40	160
35		160	200				40
36		160				200	40
37		160	160				80
38		160				160	80
39		160	120				120
40		160				120	120
41		160	80				160
42		160				80	160
43		120	240				40
44		120				240	40
45		120	200				80
46		120				200	80
47		120	160				120
48		120				160	120
49		120	120				160
50		120				120	160

[00171] Molecular weight, thermal properties, and other characteristics of the polymer blends of Examples 1-50 are given in Table 3, below.

Table 3

Ex. No.	MFR, g/10 min (2.16 kg, 230°C)	FTIR	Mw, g/mol	Mw/Mn	DSC: 1 st Heat		DSC: 2 nd Heat			Tg, °C
					Tm, °C	Hf, J/g	Tm, °C	Hf, J/g	Tm, °C (onset)	
1		54.45	43365	2.27	23.1	15.0	23.1	15.0	-34.0	-57.1
2		56.92	42001	2.19	23.8	21.8	23.8	21.8	-37.4	-56.8
3		59.95	40998	2.19	25.1	32.8	25.1	32.8	-40.1	-56.8
4		61.43	37615	2.27	28.7	36.4	28.7	36.4	-36.3	-57.1
5		64.25	35251	2.23	29.1	44.0	29.1	44.0	-34.2	-57.1
6		54.27	42868	2.30	26.6	17.1	26.6	17.1	-31.0	-57.2
7		58.11	44370	2.21	35.7	16.8	35.7	16.8	-15.0	-57.1
8		60.99	43775	2.26	39.5	34.7	39.5	34.7	-34.3	-56.9
9		64.43	42444	2.21	40.3	36.5	40.3	36.5	-26.9	-57.3
10		66.78	43449	2.21	41.5	47.6	41.5	47.6	-32.2	-56.9
11		58.99	39517	2.25	22.1	27.9	22.1	27.9	-37.5	-57.0
12		61.64	39076	2.25	25.1	29.3	25.1	29.3	-32.9	-56.8
13		63.77	37498	2.37	24.6	40.3	24.6	40.3	-37.8	-56.9
14		60.69	44150	2.19	23.7	30.5	23.7	30.5	-38.0	-56.9
15		62.85	40363	2.27	25.8	38.0	25.8	38.0	-37.3	-57.0
16		65.32	40637	2.29	30.2	44.1	30.2	44.1	-35.8	-57.0
17	5.4380	54.65			47.8	11.5	26.1	20.1	-50.7	-57.7
18	5.2340	54.81			51.9	15.8	32.0	10.6	-39.0	-57.9
19	5.0480	56.73			48.3	22.9	47.6	18.2	-37.5	-58.0
20	4.9280	56.40			52.4	18.8	51.1	15.2	-38.0	-58.1
21	5.4150	58.30			45.7	31.8	23.6	27.1	-50.4	-57.8
22	5.1410	56.42			51.5	14.5	18.0	12.6	-31.3	-57.8
23	4.9690	58.21			47.4	32.5	43.2	29.7	-49.4	-57.9
24	4.8310	57.22			51.7	21.4	51.8	16.0	-24.1	-57.9
25	4.9050	59.58			48.6	40.0	50.1	32.0	-50.4	-58.1
26	4.6580	57.37			n/a	n/a	n/a	n/a	n/a	n/a
27	5.3270	59.10			47.1	27.5	24.1	22.9	-39.3	-57.8
28	5.0790	58.58			49.0	16.2	15.2	19.6	-41.2	-58.0
29	4.9280	60.27			48.2	33.3	41.5	20.4	-23.5	-57.7
30	4.8980	59.13			48.9	18.7	46.1	16.2	-21.7	-57.8

Table 3 Cont.

Ex. No.	MFR, g/10 min (2.16 kg, 230°C)	FTIR	Mw, g/mol	Mw/Mn	DSC: 1 st Heat		DSC: 2 nd Heat			Tg, °C
31	4.6240	60.82			49.3	26.5	49.3	23.4	-15.0	-58
32	4.5180	61.11			50.1	24.7	50.6	21.0	-14.1	-57.8
33	4.2340	63.66			51.4	43.3	52.3	26.2	-11.3	-57.9
34	4.3650	61.47			50.1	31.8	52.1	25.0	-13.4	-58.0
35	5.3000	61.30			46.6	30.7	25.1	26.2	-36.7	-57.6
36	5.0550	60.19			48.8	15.8	17.4	18.1	-32.0	-57.6
37	4.9490	62.41			47.9	34.1	30.4	26.8	-31.8	-57.7
38	4.7130	60.43			48.9	23.3	20.7	21.4	-27.2	-57.7
39	4.5570	64.59			48.1	42.7	45.9	27.1	-24.3	-57.9
40	4.6380	62.75								
41	4.2630	64.58			48.5	46.1	48.7	32.3	-27.6	-57.6
42	4.1960	62.80								
43	5.7060	61.72			49.0	23.0	23.1	27.3	-33.8	-57.7
44	4.9250	61.83								
45	5.0010	63.28			50.1	28.2	28.5	31.1	-32.0	-57.6
46	4.8630	61.82								
47	4.6630	64.36			50.4	37.6	41.0	35.6	-32.0	-57.5
48	4.3740	63.47								
49	4.3840	65.24			50.9	34.4	47.7	35.6	-21.9	-57.5
50		54.45	43365	2.27	23.1	15.0	23.1	15.0	-34.0	-57.1

[00172] Tables 2 and 3 show the compositionally disperse and crystallinity disperse blends of the ethylene-based copolymers described herein.

5 Examples 51-100

[00173] 10W-50 lubricating oil compositions were prepared comprising the ethylene-based copolymer blends of Examples 1-50. All of the lubricating oil formulations comprised the following: 52 g of a group 11 lubricating oil basestock having a viscosity of 4.5 cSt, 30.6 g of a group 11 lubricating oil basestock having a viscosity of 6.1 cSt, 1.4 g of the inventive polymer blend composition of one of Examples 1-50, 14 g of an additive package (Infineum D3426), 0.7 g of a magnesium sulfonate additive having a base number of 400 (Infineum 9340), 1.0 g of a calcium sulfonate additive having a base number of 300 (Infineum 9330), and 0.3 g of a pour point depressant (Infineum V387). Viscosity characteristics of the resulting compositions were tested as follows. Kinematic viscosity (KV) at 100°C was

determined according to ASTM D445-5. Apparent viscosity was measured using a cold cranking simulator (CCS) at -20°C and -25°C according to ASTM D5293-4 and ASTM D5293-5, respectively. Yield stress and viscosity were determined using a mini rotary viscometer (MRV) at -25°C and -30°C according to ASTM D4684-4 (-25°C) and ASTM D4684-5 (-30°C). Results of these tests are reported in Table 4, below.

Table 4

Ex. No.	KV, cSt (100°C)	CCS, cP (-20°C)	CCS, cP (-25°C)	Yield Stress, MRV (-25°C)	MRV Visc., cP (-25°C)	Yield Stress, MRV (-30°C)	MRV Visc., cP (-30°C)	Pour Point, °C	Visual Gelation Rating
51	18.11	3,320	6,490	<35	14,800	<35	40,900	-34	2
52	18.03	3,210	6,460	<35	14,300	<35	39,300	-36	4
53	17.76	3,140	6,350	<35	13,500	<35	37,900	-36	4
54	17.52	3,090	6,260	<35	12,100	<35	36,500	-35	4
55	17.47	3,040	6,200	<35	12,100	<35	36,300	-36	4
56	18.80	3,290	6,660	<35	15,000	<35	38,700	-37	0
57	18.89	3,230	6,590	<35	13,700	<35	37,600	-36	0
58	19.00	3,170	6,400	<35	12,700	<35	34,900	-36	
59	19.38	3,110	6,370	<35	10,500	<35	29,800	-38	4
60	19.43	3,050	6,400	<35	11,200	<35	32,200	-36	4
61	17.75	3,160	6,300	<35	14,300	<35	40,800	-37	4
62	17.43	3,110	6,140	<35	12,800	<35	37,700	-35	4
63	17.57	3,080	6,130	<35	12,900	<35	38,700	-35	4
64	18.32	3,210	6,330	<35	13,300	<35	38,600	-36	3
65	18.40	3,140	6,310	<35	12,600	<35	35,900	-36	3
66	18.76	3,090	6,220	<35	11,900	<35	34,600	-37	3
67	18.61	3,590	7,020	<35	15,800	<35	40,600	-38	
68	19.53	3,670	7,170	<35	16,800	<35	45,000	-35	
69	18.77	3,550	7,050	<35	15,400	<35	40,600	-38	
70	19.12	7,080	7,080	<35	16,600	<35	42,200	-37	
71	19.38	3,580	7,140	<35	18,500	<35	50,000	-36	
72	18.63	3,480	7,000	<35	15,500	<35	43,000	-33	
73	18.85	3,480	6,840	<35	14,300	<35	43,200	-34	
74	19.21	3,480	6,950	<35	14,400	<35	43,100	-31	
75	19.29	3,460	6,960	<35	15,100	<35	48,000	-35	
76	18.21	3,390	6,850	<35	13,800	<35	40,400	-33	

Table 4 Cont.

Ex. No.	KV, cSt (100°C)	CCS, cP (-20°C)	CCS, cP (-25°C)	Yield Stress, MRV (-25°C)	MRV Visc., cP (-25°C)	Yield Stress, MRV (-30°C)	MRV Visc., cP (-30°C)	Pour Point, °C	Visual Gelation Rating
77	18.75	3,420	6,920	<35	14,100	<35	40,300	-31	
78	19.00	3,400	6,870	<35	14,000	<35	42,300	-32	
79	19.28	3,410	6,960	<35	14,500	<35	46,300	-30	
80	18.20	3,340	6,800	<35	13,100	<35	39,500	-34	
81	18.57	3,350	6,830	<35	12,500	<35	36,600	-32	
82	18.98	3,360	6,800	<35	12,500	<35	37,600	-36	
83	19.39	3,410	6,980	<35	13,300	<35	44,300	-34	
84	18.90	3,500	6,820	<35	15,100	<35	39,700	-37	
85	19.29	3,510	6,840	<35	15,700	<35	42,300	-37	
86	19.06	3,430	6,830	<35	15,000	<35	39,900	-37	
87	19.22	3,430	6,750	<35	14,900	<35	38,800	-37	
88	19.30	3,400	6,720	<35	15,100	<35	41,800	-35	
89	19.02	3,370	6,650	<35	14,800	<35	41,200	-29	
90	19.23	3,360	6,720	<35	14,100	<35	39,200	-31	
91	19.40	3,380	6,710	<35	14,700	<35	41,100	-31	
92	19.46	3,320	6,690	<35	14,700	<35	44,500	-31	
93	19.05	3,360	6,670	<35	15,200	<35	44,700	-29	
94	19.09	3,330	6,580	<35	13,900	<35	38,100	-32	
95	19.16	3,290	6,680	<35	13,600	<35	38,500	-34	
96	19.27	3,300	6,610	<35	14,400	<35	42,900	-34	
97	19.49	3,370	6,740	<35	15,400	<70	50,700	-34	
98	19.09	3,310	6,680	<35	13,900	<35	40,500	-35	
99	19.65	3,320	6,640	<35	12,300	<35	36,600	-37	
100	19.30	3,270	6,520	<35	13,000	<35	39,400	-36	

Examples 101-125

[00174] Lubricating oil compositions were prepared comprising selected ethylene-based copolymer blends of Examples 1-50. All of the lubricating oil formulations comprised 1 wt% of the ethylene-based copolymer blend in a Group I basestock (Americas Core 150, available from Imperial Oil Ltd.) having the following lubricant properties: kinematic viscosity (KV) at 100°C (ASTM D445-5) of 5.189 cSt, KV at 40°C (ASTM D445-3) of 29 cSt (min), viscosity index (ASTM D2270) of 95 (min), flash point (ASTM D92) of 210°C (min), pour point (ASTM D97) of -15°C (max), and Noack volatility (ASTM D5800) of 20 wt% (max).

For each formulation, shear stability properties (reflected by the Kurt Orbahn (KO) test at 30 and 90 cycles) and thickening efficiency (TE) were measured. Results of these tests are reported in Table 5, below.

Table 5

Example No.	Blend No.	KO (30 cycles)	KO (90 cycles)	TE
101	1	20.54	25.04	1.98
102	2	21.00	24.60	1.95
103	3	18.90	22.96	1.92
104	4	17.82	21.59	1.88
105	5	17.02	20.21	1.86
106	6	24.06	28.19	2.04
107	7	23.25	28.35	2.03
108	8	21.41	26.25	2.05
109	9	21.36	26.03	2.10
110	10	22.44	26.03	2.10
111	11	19.42	23.51	1.92
112	12	16.31	20.55	1.87
113	13	12.69	16.99	1.85
114	14	20.75	25.09	1.96
115	15	20.62	25.09	1.99
116	16	20.11	24.62	2.04
117	17	23.24	27.53	1.98
118	27	19.79	23.42	1.93
119	37	20.15	24.07	1.98
120	43	17.90	22.22	1.91
121	18	20.70	25.58	1.98
122	22	23.93	28.57	2.06
123	28	22.63	27.08	2.06
124	38	20.58	26.95	2.08
125	46	20.81	25.96	2.07

5

[00175] Certain embodiments and features have been described using a set of numerical upper limits and a set of numerical lower limits. It should be appreciated that ranges from any lower limit to any upper limit are contemplated unless otherwise indicated. Certain lower limits, upper limits and ranges appear in one or more claims below. All numerical values are "about" or "approximately" the indicated value, and take into account experimental error and variations that would be expected by a person having ordinary skill in the art.

10

[00176] Various terms have been defined above. To the extent a term used in a claim is not defined above, it should be given the broadest definition persons in the pertinent art have given that term as reflected in at least one printed publication or issued patent. Furthermore, all patents, test procedures, and other documents cited in this application are fully
5 incorporated by reference to the extent such disclosure is not inconsistent with this application and for all jurisdictions in which such incorporation is permitted.

[00177] While the foregoing is directed to embodiments of the present invention, other and further embodiments of the invention may be devised without departing from the basic scope thereof, and the scope thereof is determined by the claims that follow.

CLAIMS

We claim:

1. A polymer blend composition comprising a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, wherein:
 - 5 (a) the first copolymer has an ethylene content from about 35 to about 55 wt%;
 - (b) the second copolymer has an ethylene content from about 55 to about 85 wt%;
 - (c) the third copolymer has an ethylene content from about 65 to about 85 wt%;
 - (d) the ethylene content of the second copolymer is at least about 15 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third
10 copolymer is at least about 5 wt% greater than the ethylene content of the second copolymer;
 - (e) the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000;
 - (f) the ratio of the melt index of the first copolymer to the melt index of the second
15 copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and
 - (g) the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.
- 20 2. The polymer blend composition of claim 1, wherein the first copolymer has an ethylene content from about 40 to about 55 wt%, the second copolymer has an ethylene content from about 55 to about 73 wt%, and the third copolymer has an ethylene content from about 70 to about 85 wt%.
3. The polymer blend composition of claims 1 or 2, wherein the first copolymer has an
25 ethylene content from about 45 to about 53 wt%, the second copolymer has an ethylene content from about 65 to about 73 wt%, and the third copolymer has an ethylene content from about 71 to about 85 wt%.
4. The polymer blend composition of any of claims 1-3, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting
30 of C₃-C₂₀ alpha-olefins.
5. The polymer blend composition of any of claims 1-4, wherein the ethylene content of the second copolymer is at least about 18 wt% greater than the ethylene content of the first

copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

6. The polymer blend composition of any of claims 1-5, wherein the ethylene content of the second copolymer is at least about 22 wt% greater than the ethylene content of the first
5 copolymer and the ethylene content of the third copolymer is at least about 8 wt% greater than the ethylene content of the second copolymer.

7. The polymer blend composition of any of claims 1-6, wherein the composition comprises from about 25 to about 75 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

10 8. The polymer blend composition of any of claims 1-7, wherein the composition comprises from about 35 to about 65 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

9. A polymer blend composition comprising a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, wherein:

- 15 (a) the first copolymer has a first melt heat of fusion from about 0 to about 30 J/g;
(b) the second copolymer has a first melt heat of fusion from about 30 to about 50 J/g;
(c) the third copolymer has a first melt heat of fusion from about 40 to about 85 J/g;
(d) the heat of fusion of the third copolymer is at least about 5 J/g greater than the heat of fusion of the second copolymer;
20 (e) the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000;
(f) the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0;
25 and
(g) the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

10. The polymer blend composition of claim 9, wherein the first copolymer has a first melt heat of fusion from about 0 to about 15 J/g, the second copolymer has a first melt heat
30 of fusion from about 35 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 55 to about 75 J/g.

11. The polymer blend composition of claims 9 or 10, wherein the first copolymer has a first melt heat of fusion from about 0 to about 10 J/g, the second copolymer has a first melt

heat of fusion from about 40 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 65 to about 75 J/g.

12. The polymer blend composition of any of claims 9-11, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

13. The polymer blend composition of any of claims 9-12, wherein the heat of fusion of the third copolymer is at least about 8 J/g greater than the heat of fusion of the second copolymer.

14. The polymer blend composition of any of claims 9-13, wherein the heat of fusion of the third copolymer is at least about 12 J/g greater than the heat of fusion of the second copolymer.

15. The polymer blend composition of any of claims 9-14, wherein the composition comprises from about 25 to about 75 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

16. The polymer blend composition of any of claims 9-15, wherein the composition comprises from about 35 to about 65 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

17. A lubricating oil composition comprising a lubricating oil basestock, a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer wherein:

- (a) the first copolymer has an ethylene content from about 35 to about 55 wt%;
- (b) the second copolymer has an ethylene content from about 55 to about 85 wt%;
- (c) the third copolymer has an ethylene content from about 65 to about 85 wt%;
- (d) the ethylene content of the third copolymer is at least about 5 wt% greater than the ethylene content of the second copolymer;
- (e) the first, second, and third copolymers have a weight-average molecular weight (M_w) less than or equal to about 130,000;
- (f) the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and
- (g) the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

18. The lubricating oil composition of claim 17, wherein the first copolymer has an ethylene content from about 45 to about 53 wt%, the second copolymer has an ethylene content from about 65 to about 73 wt%, and the third copolymer has an ethylene content from about 71 to about 85 wt%.

5 19. The lubricating oil composition of claims 17 or 18, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

20. The lubricating oil composition of any of claims 17-19, wherein the ethylene content of the second copolymer is at least about 18 wt% greater than the ethylene content of the first
10 copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

21. A lubricating oil composition comprising a lubricating oil basestock, a first ethylene-based copolymer, a second ethylene-based copolymer, and a third ethylene-based copolymer, wherein:

- 15 (a) the first copolymer has a first melt heat of fusion from about 0 to about 30 J/g;
(b) the second copolymer has a first melt heat of fusion from about 30 to about 50 J/g;
(c) the third copolymer has a first melt heat of fusion from about 40 to about 85 J/g;
(d) the heat of fusion of the third copolymer is at least about 5 J/g greater than the heat of fusion of the second copolymer;
20 (e) the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000;
(f) the ratio of the melt index of the first copolymer to the melt index of the second copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0;
25 and
(g) the composition comprises from about 15 to about 85 wt% of the first copolymer, based on the total weight of the first, second, and third copolymers.

22. The lubricating oil composition of claim 21, wherein the first copolymer has a first melt heat of fusion from about 0 to about 10 J/g, the second copolymer has a first melt heat
30 of fusion from about 40 to about 48 J/g, and the third copolymer has a first melt heat of fusion from about 65 to about 75 J/g.

23. The lubricating oil composition of claims 21 or 22, wherein the first, second, and third copolymers each comprise one or more comonomers selected from the group consisting of C₃-C₂₀ alpha-olefins.

24. The lubricating oil composition of any of claims 21-23, wherein the ethylene content
5 of the second copolymer is at least about 18 wt% greater than the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 6 wt% greater than the ethylene content of the second copolymer.

25. A method for making the composition of any of claims 1-16 comprising the steps of:
(i) combining the first copolymer, second copolymer and third copolymer; and (ii) forming
10 the composition, wherein:

- (a) the first copolymer has an ethylene content from about 35 to about 55 wt%;
- (b) the second copolymer has an ethylene content from about 55 to about 85 wt%;
- (c) the third copolymer has an ethylene content from about 65 to about 85 wt%;
- (d) the ethylene content of the second copolymer is at least about 15 wt% greater than
15 the ethylene content of the first copolymer and the ethylene content of the third copolymer is at least about 5 wt% greater than the ethylene content of the second copolymer;
- (e) the first, second, and third copolymers have a weight-average molecular weight (Mw) less than or equal to about 130,000;
- (f) the ratio of the melt index of the first copolymer to the melt index of the second
20 copolymer is less than or equal to about 3.0 and the ratio of the melt index of the first copolymer to the melt index of the third copolymer is less than or equal to about 3.0; and
- (g) the composition comprises from about 15 to about 85 wt% of the first copolymer,
25 based on the total weight of the first, second, and third copolymers.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2011/043190

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08L23/08 C08L23/14 C10M143/04
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
C08L C10M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	WO 2010/126721 A1 (EXXONMOBIL CHEM PATENTS INC [US]; DATTA SUDHIN [US]; CANICH JO ANN MAR) 4 November 2010 (2010-11-04) claims 1-25; tables 7,8 -----	1-25

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search 9 September 2011	Date of mailing of the international search report 16/09/2011
---	--

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Knutzen-Mies, Karen
--	---

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2011/043190

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2010126721 A1	04-11-2010	US 2010273936 A1	28-10-2010
		WO 2010129151 A1	11-11-2010
		WO 2010126720 A1	04-11-2010
