

(19)  
(12)

(KR)  
(B1)

(51) 。 Int. Cl. <sup>6</sup>  
C04B 35/46

(45)  
(11)  
(24)

2003 01 24  
10 - 0353863  
2002 09 10

(21) 10 - 1998 - 0037412  
(22) 1998 09 10

(65) 2000 - 0019365  
(43) 2000 04 06

(73) 206

가 161

(72) 201 1302  
105 1005  
21 908  
2 1609  
109 104  
107 1003

(74)  
:

(54)

25 43wt% TiO<sub>2</sub>, 39 57wt% ZrO<sub>2</sub> 7 28wt% SnO<sub>2</sub> 92 99.8wt% ,  
BaCO<sub>3</sub>, BaTiO<sub>3</sub>, BaZrO<sub>3</sub>, SrCO<sub>3</sub>, SrTiO<sub>3</sub> SrZrO<sub>3</sub> 0.2 8wt% 가  
; 1250 1400 , 가  
,

1

, TiO<sub>2</sub>, ZrO<sub>2</sub>, SnO<sub>2</sub>, BaCO<sub>3</sub>, BaTiO<sub>3</sub>, BaZrO<sub>3</sub>, SrCO<sub>3</sub>, SrTiO<sub>3</sub>, SrZrO<sub>3</sub>

1

2

o)

(Qx f

frequency : f<sub>o</sub>) (dielectric constant : ε<sub>r</sub>) (quality factor : Q)가 (resonant fre  
(circuit) 가 (bandpass filter) tm

esonant frequency : f<sub>f</sub>)가 -5ppm/ +5ppm/ (temperature coefficient of r

(solid - state reaction) 가 38 (Zr,Sn)TiO<sub>4</sub>가 (relative density)가 90% (Zr,Sn)TiO  
(sintering temperature)가 [ ;

Shinich Hirano, Takashi Hayashi, and Akiyoshi Hattori, " Chemical Processing and Microwave Characteris  
tics of (Zr,Sn)TiO<sub>4</sub> Microwave Dielectrics," J. Am. Ceram. Soc., 74 [6] 1320 - 1324 (1991)].

(Zr,Sn)TiO<sub>4</sub> 1600  
가 (additives)

No. 4,102,696 22 43wt% TiO<sub>2</sub>, 38 58wt% ZrO<sub>2</sub>, 9 26wt% SnO<sub>2</sub> La<sub>2</sub>  
O<sub>3</sub>, CoO, ZnO 가 0.2 17wt% 가 ,  
1600 La<sub>2</sub>O<sub>3</sub>, CoO, ZnO 가 가 1320

No. 4,665,041 22 43wt% TiO<sub>2</sub>, 38 58wt% ZrO<sub>2</sub>, 9 26wt% SnO<sub>2</sub>  
7wt% ZnO , 10wt% NiO, Nb<sub>2</sub>O<sub>5</sub>, Ta<sub>2</sub>O<sub>5</sub>, WO<sub>3</sub>, Sb<sub>2</sub>O<sub>5</sub> 가 7wt%  
가 1350 1450

No. 5,132,258  
 $x$   $0.30$   $y$   $0.60, 0.25$   $z$   $0.60, 0.025$   $x+y+z=1$   $xT$   
 $iO_2 - yZrO_2 - zSnO_2$  MnO, Al<sub>2</sub>O<sub>3</sub>, CuO, Li<sub>2</sub>O 가 5wt%  
 가 Ga<sub>2</sub>O<sub>3</sub> 3wt% 가 Nb<sub>2</sub>O<sub>5</sub> Ta<sub>2</sub>O<sub>5</sub> 10wt% 가 , 가 ZnO  
 5wt% 가 1350 1450 .

1250 1400 가 가

ZrO<sub>2</sub> 7 28wt% SnO<sub>2</sub> 92 99.8wt% , BaCO<sub>3</sub>, BaTiO<sub>3</sub>, BaZrO<sub>3</sub>, SrCO<sub>3</sub>, SrTiO<sub>3</sub>  
 SrZrO<sub>3</sub> 0.2 8wt% 가 ;  
 1250 1400 .

33 44 , (Q x f<sub>o</sub>) 27,000GHz , 가 - 1  
 Oppm/ +40ppm/ .

(ratio) 가 . TiO<sub>2</sub>  
 25wt% 가 , TiO<sub>2</sub> 43wt%  
 가 (+) , ZrO<sub>2</sub> SnO<sub>2</sub> 57wt% 28wt% ZrO<sub>2</sub>  
 39wt% 가 , SnO<sub>2</sub> 7wt%  
 가 , BaCO<sub>3</sub> 가 8wt% 가  
 가 (-) 가 , SrCO<sub>3</sub> 가 8wt% 가 가 .  
 BaCO<sub>3</sub> SrCO<sub>3</sub> 가 가 0.2wt% .

, 가 가  
 , 가 .

, 1 (high purity) ZrO<sub>2</sub>, SnO<sub>2</sub>, TiO<sub>2</sub>, BaCO<sub>3</sub> SrCO<sub>3</sub> 25  
 , ( r), , (Q x f<sub>o</sub>)  
 ( f) .

시료 번호	TiO <sub>2</sub>	ZrO <sub>2</sub>	SnO <sub>2</sub>	BaCO <sub>3</sub>	SrCO <sub>3</sub>	$\epsilon_r$	$Q \times f_0$	$\tau_f$
*1	48	44	8	0.5	0.5	46.3	48300	+93
2	43	49	8	0.5	0.5	41.7	37400	+24
*3	42	36	22	0.5	0.5	37.8	40200	+51
4	39	54	7	0.5	0.5	38.4	33500	+21
5	38	47	15	0.5	0.5	37.7	47800	0
6	38	47	15	1.0	0.0	37.1	46600	-1
7	38	47	15	0.0	1.0	38.3	45900	+1
*8	38	47	15	1.0	9.0	43.6	31000	+42
9	38	41	21	0.5	0.5	36.2	53600	-8
10	38	41	21	0.5	2.0	38.4	51300	+1
*11	38	41	21	9.0	1.0	33.4	22500	-23
12	37	35	28	0.5	0.5	41.3	47800	+32
*13	37	28	35	0.5	0.5	45.7	23700	+185
*14	34	59	7	0.5	0.5	37.8	35100	+36
15	34	52	14	0.5	0.5	35.6	41200	+1
16	33	46	21	0.5	0.5	36.2	43100	-7
17	33	40	27	0.5	0.5	35.6	41000	+4
*18	33	33	34	0.5	0.5	32.1	26300	+78
19	29	57	14	0.5	0.5	34.7	37100	+22
20	29	50	21	0.5	0.5	34.2	45200	-4
21	29	44	27	0.5	0.5	34.1	42800	-7
*22	28	38	34	0.5	0.5	31.3	24600	+41
23	25	55	20	0.5	0.5	33.5	27300	+2
24	25	49	26	0.5	0.5	33.4	44500	-8
*25	21	53	26	0.5	0.5	32.8	36700	-11

(high purity) ZrO<sub>2</sub>, SnO<sub>2</sub>, TiO<sub>2</sub>, BaCO<sub>3</sub>, SrCO<sub>3</sub>, S  
 (ZrO<sub>2</sub> ball) (deionized water)  
 (weighing) (ball milling)  
 16 2  
 1150  
 (PVA) 가 (mortar) 150 (mesh) (screen) 가 12mm,  
 (cakes) 1000 2500kg/cm<sup>2</sup> (polishing)  
 8mm 1  
 250 1400 4

25 (open cavity method) 25 (unloaded) " Hakki - Coleman" 1

[ 1 ]

$$\tau_t = \frac{f_{85} - f_{25}}{f_{25} \times \Delta T} \times 10^6 \text{ (ppm/}^\circ\text{C)}$$

1 f<sub>85</sub> f<sub>25</sub> 85 25 T 60  
 1 \* 27,000GHz 가 - 10ppm/ 가 33 +40ppm/  
 1 5 9 (Q x f<sub>o</sub>) 2

BaCO<sub>3</sub> SrCO<sub>3</sub> 가 , 25 43wt% TiO<sub>2</sub>, 39 57wt% ZrO<sub>2</sub>, 7 28wt% SnO<sub>2</sub>  
 1400 Hz , 가 33 44 , (Q x f<sub>o</sub>) 27,000G  
 BaZrO<sub>3</sub> 가 , SrCO<sub>3</sub> SrTiO<sub>3</sub> SrZrO<sub>3</sub> 가 , BaCO<sub>3</sub> BaTiO<sub>3</sub>


(57)

1.

25 43wt% TiO<sub>2</sub>, 39 57wt% ZrO<sub>2</sub> 7 28wt% SnO<sub>2</sub> 92 99.8wt% , BaCO<sub>3</sub>,  
 BaTiO<sub>3</sub>, BaZrO<sub>3</sub>, SrCO<sub>3</sub>, SrTiO<sub>3</sub> SrZrO<sub>3</sub> 0.2 8wt% 가

1250 1400

1



2

