

(19) **DANMARK**

(10) **DK/EP 2289573 T3**



(12)

Oversættelse af  
europæisk patentskrift

Patent- og  
Varemærkestyrelsen

- 
- (51) Int.Cl.: **A 61 L 29/08 (2006.01)** **A 61 L 29/14 (2006.01)**
- (45) Oversættelsen bekendtgjort den: **2017-02-06**
- (80) Dato for Den Europæiske Patentmyndigheds bekendtgørelse om meddelelse af patentet: **2016-10-26**
- (86) Europæisk ansøgning nr.: **10195654.8**
- (86) Europæisk indleveringsdag: **2007-01-30**
- (87) Den europæiske ansøgnings publiceringsdag: **2011-03-02**
- (30) Prioritet: **2006-02-01 US 764151 P**
- (62) Stamansøgningsnr: **07762800.6**
- (84) Designerede stater: **AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK TR**
- (73) Patenthaver: **Hollister Incorporated, 2000 Hollister Drive, Libertyville, IL 60048-3781, USA**
- (72) Opfinder: **Gilman, Thomas H., 7209 Ridge Court, Spring Grove, IL 60081, USA**
- (74) Fuldmægtig i Danmark: **HØIBERG P/S, Adelgade 12, 1304 København K, Danmark**
- (54) Benævnelse: **Fremgangsmåder til påføring af et hydrofilt overtræk på et substrat samt substrater med et hydrofilt overtræk**
- (56) Fremdragne publikationer:  
**WO-A-98/58990**  
**US-A- 4 589 873**  
**US-A- 4 840 851**  
**US-A- 4 876 126**  
**US-A- 5 331 027**  
**US-A- 5 670 558**  
**US-A- 6 048 620**



## DESCRIPTION

### FIELD OF THE INVENTION

[0001] This invention relates to methods of applying to a substrate a hydrophilic coating that becomes lubricious when activated with water or water vapor, and to substrates having such a hydrophilic coating.

### BACKGROUND

[0002] In the medical field, and in other fields as well, there has developed a need for substrates with surfaces that become lubricious upon contact with water. A main use of lubricious materials involves catheters, catheter guide wires, and other medical devices that are meant to be inserted into the body. The lubricious nature of such materials allows the insertion (and subsequent removal) of a catheter or other medical device to be accomplished with minimum resistance, thereby reducing discomfort and possible injury.

[0003] In many cases, it is easy to prepare a functional lubricious coating for a substrate surface. However, it is more difficult to prepare a lubricious coating that is securely anchored to the substrate surface. Secure anchoring of a lubricious coating to a substrate surface is generally desirable, and particularly useful in the medical field, where secure anchorage of the coating is often an important requirement.

[0004] U.S. Patent 4,642,267 to Creasy et al. discloses a hydrophilic polymer blend comprising a thermoplastic polyurethane and a poly(N-vinyl lactam). When used as a coating material, the polymer blend components are co-dissolved in an organic solvent capable of solubilizing both polymers, a substrate is dip coated in the solution, and the solvent is then driven off by a drying process so as to form a hydrophilic coating on the substrate surface. However, the coating attachment to the substrate is considered to lack the security desired. Another disadvantage of the '267 patent is that high boiling point and potentially toxic solvents are used to deliver the coating formulation, and thus significant costs must be incurred to drive off the solvent residuals from the coated product so as to obtain the desired biocompatibility.

[0005] U.S. Patent 5,702,754 to Zhong discloses coating a substrate surface with a polymer having reactive functional groups and an excess of cross-linking agent. The polymer is cured to form a coating. Then, a second coating comprising a hydrophilic polymer having the same type of reactive functional groups is applied thereover. When the hydrophilic polymer is then cured, the second coating becomes covalently bonded to the first coating because the first coating includes an excess of cross-linking agent thereby permitting covalent bonding between the first coating and the hydrophilic polymer. Disadvantages of this approach include the fact that multiple steps are required and multiple polymer solutions are involved. There are also significant limitations in the selection of lubricious polymers and cross-linking agents.

[0006] US5670558 discloses a process for producing a medical instrument (e.g. catheter) with surface lubricity comprising coating the matrix surface of the medical instrument with a solution containing a water-soluble or water-swellaable polymer having a reactive functional group in the molecule (e.g. a block or graft copolymer comprising vinyl pyrrolidone, (meth)acrylic acid) and insolubilizing (crosslinking) said water-soluble or water-swellaable polymer to form a layer on the surface of the medical instrument that will form a hydrogel when wetted. After coating the water-soluble or water-swellaable polymer of the matrix and increasing the temperature, the water-soluble or water-swellaable polymers will react either with themselves or with the matrix surface. In order to form a tenacious hydrogel layer on the matrix surface, it is important that an intermolecular reaction be carried out with the matrix being thoroughly impregnated with the water-soluble or water-swellaable polymer, so as to achieve an interpenetrating network.

### SUMMARY OF THE INVENTION

[0007] In one aspect, the invention provides a method of applying a lubricious hydrophilic coating to a surface of a medical device having a surface comprised at least in part of a water-swellaable material, and contacting the surface of the medical device with a solution comprising at least one of (i) a water-soluble polymer capable of being cross-linked to form a cross-linked, lubricious, hydrophilic coating and (ii) a water-soluble monomer capable of being polymerized to form a cross-linked, lubricious, hydrophilic coating. The water-soluble polymer can be cross-linked in the presence of the swollen medical device surface to provide a cross-linked coating that is entangled with and securely anchored to the medical device surface. Similarly, the monomer

can either form a crosslinked hydrogel network as it is polymerized, or can be polymerized and then subsequently cross-linked, in the presence of the swollen medical device surface, to provide a cross-linked coating that is entangled with and securely anchored to the surface of the medical device. The medical device includes a first or outer layer comprising a water-swellaible material. The medical device may further include an optional second or support layer, which comprises non-water-swellaible materials and/or water-swellaible materials.

**[0008]** In another aspect, the invention provides a medical device having a hydrophilic coating, such medical device, prior to coating, having a surface comprised at least in part of a water-swellaible material having swollen and non-swollen states, and the coating comprises an interpenetrating polymer network disposed on at least a part of the surface, the interpenetrating polymer network formed by at least one of (i) a water-soluble polymer capable of being cross-linked to form a cross-linked, lubricious, hydrophilic coating and (ii) a water-soluble monomer capable of being polymerized to form a cross-linked lubricious, hydrophilic coating, in the presence of the swollen state of the surface of the medical device, so as to secure the hydrophilic coating to the surface.

#### **DETAILED DESCRIPTION**

**[0009]** One aspect of the invention relates to methods of applying a lubricious, hydrophilic coating to a substrate, which is a medical device. An additional aspect of the invention relates to medical devices having such a lubricious, hydrophilic coating.

**[0010]** As used herein, the term "lubricious coating" refers to a coating that provides a substrate surface having a coefficient of friction value less than about 0.3, less than about 0.1, and/or less than about 0.05, for example, 0.03, or even 0.01.

**[0011]** The invention involves creating an interpenetrating polymer network *in situ* on a substrate surface. For example, a substrate surface comprising a water-swellaible material is contacted with a solution comprising a water-soluble hydrophilic polymer capable of being cross-linked to form a cross-linked, lubricious hydrophilic coating. Alternatively, a water-soluble monomer, either capable of being polymerized to form a cross-linked, lubricious, hydrophilic coating, or of being polymerized and then cross-linked to form a cross-linked, lubricious, hydrophilic coating, may be used in place of, or in addition to, the water-soluble hydrophilic polymer. The coating is typically then cured, for example, by exposure to UV light, in order to cross-link the water-soluble polymer and/or polymer formed from the water-soluble monomer.

**[0012]** The use of one or more water-soluble polymers is typically preferred relative to the use of one or more water-soluble monomers, however, particularly for medical applications, because residual unpolymerized monomer can present biocompatibility issues for medical device applications.

**[0013]** Because the water-swellaible material of the substrate swells in the presence of water and/or alcohol, it is believed to become physically entangled with the water-soluble hydrophilic polymer before cross-linking, and those entanglements are locked in during cross-linking. Thus, a coating comprising the interpenetrating polymer network is formed by polymerizing the water-soluble polymer in the presence of the water-swellaible substrate surface when the water-swellaible substrate surface is in a swollen state, and results in the lubricious coating being securely anchored to the substrate (after cross-linking thereof). Essentially, the method allows two hydrogels to be linked together mechanically on a molecular scale.

**[0014]** Advantageously, the hydrophilic coating can be secured to the surface without the need for covalent interactions between the hydrophilic coating and the first layer. Another advantage is that the coating formulation can be carried using solvents such as water and lower alcohols, which are inexpensive, biocompatible, and relatively easy to drive off from the coated product. Still another advantage is the versatility of the invention; the invention will provide secure anchorage for any hydrophilic coating formed from a water-soluble polymer and/or water-soluble monomer, which can be coated from an aqueous or alcohol based solution, without the need for a primer layer or other polymer solution based anchorage means. This versatility allows a wide number of polymer / cross-linking agent systems and/or monomer / initiator / cross-linking systems to be utilized, and thus for an optimal system to be implemented for any given application.

**[0015]** In one embodiment, the terms "well-anchored" or "securely anchored" refers to a coating that, after an abrasion protocol is conducted on the substrate carrying the coating, results in a substrate having a final coefficient of friction value, when the coating is activated, for example, by water immersion, that is not more than ten times, not more than five times, and/or not more than two times the original coefficient of friction value prior to abrasion. A suitable abrasion protocol includes passing a coated tube through a hole which is about 10% smaller diameter than the outside diameter of the tubing 100 times, while keeping the coating wet during the abrasion cycles. After this abrasion protocol, the tube is immersed in deionized water for about 30 seconds

so as to activate the coating, and the coefficient of friction can be determined using standard means.

**[0016]** A substrate, such as a catheter tube, to be coated by the methods of this invention, is formed in a way that provides it with a surface or surface layer comprised at least in part of a water-swellaible material. That may be accomplished in a variety of ways including but not limited to coextruding a substrate having a first or outer layer comprising any suitable water-swellaible material, and a second or inner support layer comprised of non-water-swellaible materials and/or water-swellaible materials.

**[0017]** Generally, any water swellaible-materials or mixtures thereof could be used for the first or outer layer. Suitable water-swellaible materials include but are not limited to water-swellaible polyamide-based copolymers, water-swellaible polyester-based copolymers, water-swellaible urethane-based copolymers, and mixtures thereof. Any of a variety of thermoplastic polymers, thermoplastic elastomers, and/or thermoplastic alloys, which are capable of swelling in the presence of water (e.g., an aqueous solution) may be used. In general, such water swellaible polymers will also swell in lower alcohols such as methanol, ethanol, propanol, isopropanol, butanol, and the like. Higher alcohols such as hexanol and octanol may also be used, but lower alcohols are typically preferred because of their increased volatility relative to water.

**[0018]** Preferably, the first layer is comprised of a water-swellaible thermoplastic elastomer comprising a block copolymer having rigid and flexible blocks. Suitable rigid blocks include polyamide blocks, polyester blocks, and polyurethane blocks, but other rigid polymer blocks may be used. The rigid block is preferably either glassy or crystalline at room temperature. Suitable flexible blocks include flexible polyether blocks such as flexible polyethylene oxide blocks, flexible poly-N-vinyl lactam blocks such as flexible polyvinylpyrrolidone blocks, flexible polyalcohol blocks, and flexible polyacid blocks. Of course, other flexible blocks could also be used.

**[0019]** Suitable water-swellaible thermoplastic elastomers include but are not limited to polyether/polyamide block elastomers such as those sold under the PEBAX<sup>®</sup> trade name (Arkema, PA), for example, such as PEBAX<sup>®</sup> 1647, PEBAX<sup>®</sup> 1074, and PUBAX<sup>®</sup> MX1652, and polyester elastomers such as those sold under the HYTEL<sup>®</sup> trade name (Du Pont de Nemours, DE), for example, such as HYTEL<sup>®</sup> 8171 and HYTEL<sup>®</sup> 8206. Other suitable water-swellaible thermoplastic elastomers include but are not limited to thermoplastic polyurethanes such as polyether thermoplastic polyurethanes sold under the ESTANE<sup>®</sup> and the TECOPHILIC<sup>®</sup> trade names (Noveon Inc., OH) and polyester thermoplastic polyurethanes such as those sold under the ESTANE<sup>®</sup> and CARBOTHANE<sup>®</sup> trade names (Noveon Inc., OH).

**[0020]** The substrate can be made entirely from a water-swellaible material. Polymer blends including at least one water-swellaible material can alternatively be used. Surprisingly, even polymer blends where a water-swellaible material comprises only a minority of the polymer blend will provide securely anchored hydrophilic coatings. This allows flexibility in designing substrates, for example, as a homoextrusion that will have the mechanical properties needed for a given application. For example, tubing made of 40 weight percent (wt.%) PEBAX<sup>®</sup> 1074 (a water-swellaible thermoplastic elastomer) and 60 wt.% PEBAX<sup>®</sup> 3533 (a non-water-swellaible thermoplastic elastomer) has desirable properties for a urinary catheter application, and provides many or all of the advantages of this invention.

**[0021]** Alternatively, the substrate can have an outer layer made from a water-swellaible material, or an outer layer made from a blend comprised of water-swellaible and non-water-swellaible materials. The substrate can then have an inner or support layer comprised of one or more non-water-swellaible materials. Of course, the inner or support layer may be made from or further include one or more water-swellaible materials.

**[0022]** As used herein, the term "water-swellaible" generally refers to a material that swells in the presence of water or alcohol. In various embodiments, the term refers to a material that increases in at least one dimension by at least 0.5%, at least 1%, at least 2%, at least 5%, at least 10%, at least 25%, or even greater when immersed in water for a period of approximately 90 minutes. In accordance with the foregoing embodiments, a 25.4 mm (1 inch) by 25.4 mm (1 inch) by 0.0254 mm (1 mil) square of material can be immersed in water for a period of 90 minutes, and the increase in the height or length can be determined relative to the original height or length so as to ascertain whether a certain material swells sufficiently to be considered a water-swellaible material in accordance with the invention. If so, the material can generally be considered suitable for use as a water-swellaible material in the invention.

**[0023]** Generally, any material can be used in forming the optional second or support layer, but materials capable of being extruded or otherwise melt-processed are generally preferred. Suitable materials for use in the optional second or support layer include but are not limited to thermoplastic resins, such as, for example, olefin polymers, particularly, polyethylenes, polypropylenes, polyvinylchlorides, polytetrafluoroethylenes, polyvinylacetates, polystyrenes, polyesters, polyurethanes,

polyamides, other suitable polymers, and mixtures thereof. Metals, ceramics, and other materials may also be used as the support layer, but then the outer layer needs to be affixed or coupled to the second layer by a mechanism different than co-extrusion, for example, by spin-casting, dip-coating, wire extrusion coating, or otherwise affixing, coupling, or adhering the water-swellaable surface layer (or substrate comprising same) to the second layer.

**[0024]** The substrate can be a medical device. Exemplary medical devices that may be coated with the lubricious coatings in accordance with the invention include but are not limited to contact lenses, medical implants including but not limited to pacemakers and wire leads for same, intravascular implants including but not limited to arterial stents, and catheters including but not limited to urinary catheters, fecal catheters, catheters for administration of intravenous fluids, medications, and nutrition, and coronary catheters such as angioplasty catheters. Further still, in certain medical device applications it may be desirable to incorporate a drug into the coating solution, or to add a drug after formation of the coating on the medical device. For example, stents having a coating in accordance with the invention can comprise a drug, for example, taxol to prevent late stenosis, or heparin to prevent the formation of a thrombus.

**[0025]** Additionally, non-medical device applications of the invention can also be envisioned where surfaces having a low coefficient of friction in a wet environment are desired because the invention can provide a highly lubricious coating to any product that is used in a wet environment. Possible non-limiting examples include marine uses, for example, such as wet suits or boat hulls where the coating could be applied to reduce drag.

**[0026]** The untreated substrate is typically dipped or otherwise coated with a polymer solution in which the coating polymer is dissolved in water, alcohol, or a solution containing both water and alcohol. If a catheter is being coated, a mandrel can be inserted into the catheter structure in order to prevent any coating solution from contacting and/or coating the inside of the catheter when the coating solution is applied.

**[0027]** Any suitable hydrophilic polymer capable of being cross-linked and of swelling and becoming lubricious when exposed to water or water vapor may be used to provide the hydrophilic coating. Upon being cross-linked, the network of the coating polymer forms an interpolymer with the swollen water-swellaable material, for example, with the flexible (or soft) blocks of the substrate surface block polymer, resulting in a coating that is securely anchored to the substrate. Suitable water-soluble hydrophilic polymers include but are not limited to polyacrylic acids, acrylic acid copolymers such as acrylamide/acrylic acid copolymers, polyvinylpyrrolidones, polyvinylalcohols, water-soluble polymers containing carboxylic acid functional groups, and mixtures thereof. Other water-soluble polymers that can be cross-linked to form a hydrophilic coating may also be used.

**[0028]** Similarly, any suitable hydrophilic monomer capable of being polymerized to form a cross-linked network and becoming lubricious when exposed to water or water vapor may be used to provide the hydrophilic coating. Suitable water-soluble hydrophilic monomers that can be used include but are not limited to vinyl monomers, for example, vinyl alcohols, vinylpyrrolidones, acrylamides, methacrylates, acrylic acids, and mixtures thereof. Some of these can be copolymerized with multifunctional monomer to form a network *in situ*, others can be polymerized and subsequently cross-linked using methods well known in the art. Various initiators, for example, photoinitiators including but not limited to benzophenone can be used to polymerize the monomers.

**[0029]** An important advantage of this method is that it is relatively easy to prepare a substrate with a securely anchored hydrophilic coating. Since the outer layer of the substrate generally includes a thermoplastic polymer, known manufacturing methods that are uncomplicated, direct, and economical, such as extrusion, co-extrusion, or injection molding, may be used to produce a substrate having a water swellaable surface. The coating method is applicable to any system of hydrophilic coating polymer and cross-linking method that can be achieved using a water- or alcohol-based solvent system. Similarly, the coating method is applicable to any system of hydrophilic monomer, initiator, and cross-linking method that can be achieved using a water- or alcohol-based solvent system.

**[0030]** Suitable cross-linking agents are well known in the art and include but are not limited to UV activatable cross-linking agents, carbodiimides, aziridines, melamine formaldehydes, and multifunctional carboxylic acid cross-linking agents. Exemplary UV activatable cross-linking agents include polymeric hydroxyl ketones sold under the ESACURE™ trade name (Sartomer Company, PA), for example, ESACURE™ KIP 150 and ESACURE™ ONE. Exemplary carbodiimide cross-linking agents are sold under the CARBODILITE™ trade name (Nisshinbo Industries, Inc., JP), for example, CARBODILITE™ V-02-L2 and CARBODILITE™ E-02. Exemplary aziridine cross-linking agents are sold under the cross-linker CX-100 trade name (DSM NeoResins, DSM, NL). Heat and/or light can also be used to cross-link some water-soluble polymers.

**[0031]** The methods of applying a hydrophilic coating to a substrate and substrates having such a hydrophilic coating in accordance with the invention can be better understood in light of the following examples. However, the foregoing description and

the following examples are merely illustrative, and therefore no unnecessary limitations should be understood therefrom as numerous modifications and variations are expected to occur to those skilled in the art.

## **EXAMPLE 1**

[0032] A coating polymer solution was prepared in an approximately 70:30 weight/weight isopropyl alcohol/water solvent system, where the polymer was polyvinylpyrrolidone K-90 at about 9 wt./vol. Included in the solution was about 0.03 wt.% UV activatable cross-linking agent (ESACURE™ KIP 150, Sartomer).

[0033] A thermoplastic substrate was employed in the form of a coextruded tube having an outside diameter of about 4.57 mm (0.180 inches) and an inside diameter of about 3.12 mm (0.123 inches). The tube had an outer layer of about 0.076 mm (0.003 inches) thick that was a blend of a polyether/polyamide block elastomer (PEBAX® 1074, a water-swellaible thermoplastic elastomer available from Arkema, PA) with an ethylene acid copolymer resin (NUCREL® 2806, a non-water-swellaible thermoplastic elastomer available from Du Pont de Nemours, DE) at a weight ratio of about 40:60. The inner layer of the tube was a blend of thermoplastic, non-water-swellaible resins designed to give the desired mechanical properties to the overall tube structure. The tube was dipped in the coating solution and held therein for about 10 minutes prior to withdrawal. After withdrawal, the tube was air dried for about 30 minutes. Thereafter, the coated tube was exposed to UV light for about 5 minutes.

[0034] The tube with its cured coating was immersed in deionized water for 30 seconds. At that point, the surface of the tube was found to be highly lubricious, and the lubricious coating was securely adhered to the tube.

## **EXAMPLE 2**

[0035] Another approach is to use a separate, second solution that contains a cross-linking agent for the coating polymer. The second solution can be applied to the substrate having a water-swellaible outer surface either before, or after, the coating polymer solution is applied. After both solutions have been applied, the coating is then cross-linked.

[0036] A coextruded tube was prepared having an outer layer of a polyether/polyamide block elastomer (PEBAX® 1074, Arkema, PA), and an inner layer of a polyether/polyamide block elastomer (PEBAX® 2533, a non-water-swellaible thermoplastic elastomer available from Arkema, PA). The tube was first dipped in an approximately 70:30 weight/weight isopropyl alcohol/water solution containing about 12wt.% of a carbodiimide cross-linking agent (CARBODILITE® V-02-L2, Nisshinbo, Japan), and held therein for ten minutes prior to withdrawal. The tube was then air dried for ten minutes, subsequently dipped in an approximately 70:30 weight/weight isopropyl alcohol/water solution containing about 7.5 wt.% of a water-soluble polymer containing carboxylic acid functional groups (GANTREZ™ S-97BF, ISP Technologies, Inc.), and then withdrawn immediately. After withdrawal, the tube was air dried for ten minutes.

[0037] The water-soluble polymer of this example is a methyl vinyl ether copolymer with maleic anhydride where the anhydride has been hydrolyzed into a diacid. The acid groups can be cross-linked by the carbodiimide cross-linking agent.

[0038] Curing was accomplished by heating the tubing to approximately 70° C for about 20 minutes in a conventional oven. The coating was neutralized by dipping it in a buffer solution. The resulting tube with its cured coating was then dipped in deionized water for 30 seconds. The surface of the wetted tube was slippery and the coating was securely adhered to the tube.

## **EXAMPLE 3**

[0039] A thermoplastic substrate was employed in the form of a coextruded tube having an outside diameter of about 4.60 mm (0.181 inches) and an inside diameter of about 3.10 mm (0.122 inches) The tube had an outer layer of about 0.076 mm (0.003 inches) thick, with the inner layer accounting for the balance of the tube. The inner tube layer comprised a blend of an ethylene octene copolymer (EXACT™ 5371, ExxonMobil Chemical Company, ExxonMobil, TX) with an ethylene acid copolymer resin (NUCREL® 2806, Du Pont de Nemours, DE) at a weight ratio of approximately 20:80, and the outer tube layer comprised a blend of a polyether/polyamide block elastomer (PEBAX® 1074, Arkema, PA) with an ethylene acid copolymer resin (NUCREL® 2806, Du Pont de Nemours, DE) at a weight ratio of approximately 40:60.

[0040] The tubing was coated by dipping in an approximately 70:30 weight/weight isopropyl alcohol/water solution containing about 5.5 wt.% polyvinylpyrrolidone K-90 (ICI Chemicals, England) and about 0.11 wt.% ESACURE™ One (Sartomer, PA). The tubing was held in the coating solution for about 5 minutes in this solution and then withdrawn. After withdrawal, the coated tubing was air dried for about 50 minutes (at room temperature). Thereafter, the coated tube was exposed to UVC light for approximately 2.5 minutes.

[0041] The resulting tube with its cured coating was then immersed in deionized water for about 30 seconds. At that point, the surface of the tube was found to be highly lubricious, having an average coefficient of friction (n = 12 samples tested) of about 0.02.

[0042] To test coating anchorage to the substrate tubing, an abrasion testing protocol was performed on the resulting coated tubing. The sample was passed through a hole in a 0.79 mm (1/32") thick silicone rubber sheet, with the hole being about 10% smaller diameter than the outside diameter of the tubing. This was done 100 times, keeping the coating wet during the abrasion testing. After this abrasion protocol, the tube was again immersed in deionized water for about 30 seconds and tested for coefficient of friction. Again, the average coefficient of friction for the samples was about 0.02.

[0043] Another group of samples was immersed for about 30 seconds in water to activate the coating, and then allowed to stand out in open air for about 10 minutes. Following this drying protocol, the average coefficient of friction (n = 12 samples tested) was about 0.02.

[0044] Still another group of samples (n = three samples) were subjected to a thermoforming process to create a bullet shaped closed tip on one end in order to make a tipped tube suitable for use as a urinary catheter. This tipped tubing was subjected to a coating process as described in this example above, except the cure was by accomplished by exposure to UVC light for a period of about 3 minutes. After immersion in deionized water for about 20 minutes, the surface of the coated tubing was very slippery and the slippery coating was well adhered to both the formed tip portion of the tubing and the straight wall portion of the tubing.

[0045] The foregoing examples demonstrate several advantages of the invention. For example, highly lubricious, highly adherent coatings have been achieved with two different water soluble polymer/cross-linker systems, and with three different substrate constructions. Example 3 further demonstrates that it is possible to thermoform a multi-layered tube while maintaining the water-swallowable properties of the outer layer surface, which allows a securely anchored coating to be achieved, even in the formed portion of the substrate. Example 3 also demonstrates that coatings made per this invention are able to maintain their slippery nature even after an extended period of air exposure. It is theorized that the water-swallowable nature of the substrate surface helps in this regard, as the substrate surface will hold water and thus perhaps contribute to the ability of the coating to maintain hydration and therefore lubricity. This attribute of the invention is particularly advantageous for intermittent urinary catheters.

## REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

### Patent documents cited in the description

- [US4642267A \[0004\]](#)
- [US5702754A \[0005\]](#)
- [US5670558A \[0006\]](#)



**PATENTKRAV**

1. Fremgangsmåde til påføring af et smørende hydrofilt overtræk på en overflade af en medicinsk indretning, hvilken fremgangsmåde omfatter, at:
- 5
- der tilvejebringes en medicinsk indretning til overtrækning, som har en overflade før overtrækning, der i det mindste delvist omfatter et vandkvældbart materiale;
- 10
- overfladen af den medicinske indretning bringes i kontakt med en opløsning for at kvælde det vandkvældbare materiale, hvilken opløsning omfatter mindst én af (i) en vandopløselig polymer, som er i stand til at blive tværbundet til dannelse af et tværbundet, smørende, hydrofilt overtræk, og (ii) en vandopløselig monomer, som er i stand til at blive polymeriseret til dannelse af et tværbundet, smørende, hydrofilt overtræk; og
- 15
- det tværbundne, smørende, hydrofile overtræk dannes,
- hvilket overtræk er viklet ind i og fast forankret til overfladen af den medicinske indretning.
- 20
2. Fremgangsmåde ifølge krav 1, hvor opløsningen omfatter mindst ét opløsningsmiddel, som er valgt fra gruppen bestående af vand, alkoholer og blandinger deraf.
3. Fremgangsmåde ifølge krav 1, hvor den medicinske indretning omfatter et første lag og et andet lag, hvor det første lag omfatter det vandkvældbare materiale.
- 25
4. Fremgangsmåde ifølge krav 3, hvor det andet lag omfatter et ikke-vandkvældbart materiale.
5. Fremgangsmåde ifølge krav 1, hvor den medicinske indretning er valgt fra gruppen
- 30
- bestående af medicinske implantater, intravaskulære implantater, katetre og kontaktlinser.
6. Fremgangsmåde ifølge krav 1, hvor det vandkvældbare materiale omfatter en blok-copolymer.
- 35

7. Fremgangsmåde ifølge krav 6, hvor blokcopolymeren er valgt fra gruppen bestående af vandkvældbare polyamidbaserede copolymerer, vandkvældbare polyesterbaserede copolymerer, vandkvældbare urethanbaserede copolymerer og blandinger deraf.
- 5 8. Fremgangsmåde ifølge krav 1, hvor den vandopløselige polymer er valgt fra gruppen bestående af polyacrylsyrer, acrylsyre-copolymerer, poly-N-vinyllactamer, polyvinylalkoholer, polyvinylalkohol-copolymerer og blandinger deraf.
9. Fremgangsmåde ifølge krav 8, hvor poly-N-vinyllactamen omfatter polyvinylpyrrolidon.  
10
10. Fremgangsmåde ifølge krav 1, hvor den vandopløselige monomer er valgt fra gruppen bestående af vinylalkoholer, vinylpyrrolidoner, acrylamider, methacrylater, acrylsyrer og blandinger deraf.  
15
11. Fremgangsmåde ifølge krav 1, hvor opløsningen desuden omfatter et tværbindingsmiddel.
12. Fremgangsmåde ifølge krav 1, hvor det hydrofile overtræk er fæstnet til overfladen uden kovalente interaktioner mellem det hydrofile overtræk og overfladen.  
20
13. Fremgangsmåde ifølge krav 11, hvor tværbindingsmidlet er valgt fra gruppen bestående af UV-aktiverbare tværbindingsmidler, carbodiimider, aziridiner, melaminformaldehyder og multifunktionelle carboxylsyre-tværbindingsmidler.  
25
14. Fremgangsmåde ifølge krav 1, som desuden omfatter, at den medicinske indretning bringes i kontakt med en opløsning, der omfatter et tværbindingsmiddel.
15. Medicinsk indretning, som har et hydrofilt overtræk, der er fremstillet ved fremgangsmåden ifølge krav 1, omfattende:  
30
- en medicinsk indretning, som har en overflade, der i det mindste delvist omfatter et vandkvældbart materiale, som har kvældede og ikke-kvældede tilstande; og

- et gennemtrængende polymernetværk, som er anbragt på overfladen, hvor det gennemtrængende polymernetværk er dannet ved at bringe overfladen af den medicinske indretning i kontakt med en opløsning for at kvælde det vandkvældbare materiale, idet opløsningen omfatter mindst én af (i) en vandopløselig polymer, som er i stand til at
- 5 blive tværbundet til dannelse af et tværbundet, smørende, hydrofilt overtræk, og (ii) en vandopløselig monomer, som er i stand til at blive polymeriseret til dannelse af et tværbundet, smørende, hydrofilt overtræk, i nærværelse af den kvædede tilstand af det vandkvældbare materiale for at fastgøre det hydrofile overtræk til overfladen.
- 10 16. Medicinsk indretning ifølge krav 15, hvor den medicinske indretning omfatter et første lag og et andet lag, hvor det første lag omfatter det vandkvældbare materiale.
17. Medicinsk indretning ifølge krav 16, hvor det andet lag omfatter et ikke-vandkvældbart materiale.
- 15 18. Medicinsk indretning ifølge krav 15, hvor den medicinske indretning er valgt fra gruppen bestående af medicinske implantater, intravaskulære implantater, katetre og kontaktlinser.
- 20 19. Medicinsk indretning ifølge krav 15, hvor det vandkvældbare materiale omfatter en blokcopolymer, som er valgt fra gruppen bestående af vandkvældbare polyamidbase-rede copolymerer, vandkvældbare polyesterbaserede copolymerer, vandkvældbare urethanbaserede copolymerer og blandinger deraf.
- 25 20. Medicinsk indretning ifølge krav 15, hvor den vandopløselige polymer er valgt fra gruppen bestående af polyacrylsyrer, acrylsyre-copolymerer, poly-N-vinyllactamer, polyvinylalkoholer, polyvinylalkohol-copolymerer og blandinger deraf.