

### 1. PRODUCT NAME

Airboard™ VB250 Insulation + Vapor Barrier

### 2. MANUFACTURER

Airfoam Industries Ltd.  
19402 - 56 Ave, Surrey BC V3S 6K4 Canada  
800.663.8162 or 604.534.8626 | www.airfoam.com

### 3. PRODUCT DESCRIPTION

Airboard™ Expanded Polystyrene (EPS) is a high-performance, closed cell, rigid foam insulation material that uses air as main ingredient. Airboard™ combines closed cell EPS rigid insulation with advanced polymeric facers for fast installation and excellent durability. The EPS insulation core is laminated on both sides with 1 mil [25.4µm] metallic reflective facers made of biaxially oriented polypropylene (BOPP) and other polymers. In Tilt-Up applications the facers act as the slip sheet to minimize bonding between the insulation, Fascia Wythe and Structural Wythe wall.

Sizes: Airboard™ EPS insulation is available in 4' widths x 8' lengths [1.22m x 2.44m] and various common thicknesses listed in Table 2 but can be custom ordered in any thickness between 1 and 6 inches to meet your requirements.

### 4. TECHNICAL DATA

#### Code Compliance

Airboard™ complies with:

- **Thermal Insulation** Canada: CAN/ULC-S701.1 Type 3,  
US: ASTM C578 Type IX, ICC-ES AC12
- **Surface Burning Characteristics:** CAN/ULC-S102.2, ASTM E84 (UL 723)


#### Material Properties

Airboard™ products exhibit the typical physical properties indicated in Table 1 and below when tested as represented.

Insulation values for given thicknesses are listed in Table 2.

#### Applicable Standards

- ASTM C177 - Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- ASTM C203 - Standard Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- ASTM C272 - Standard Test Method for Water Absorption of Core Materials for Sandwich Constructions
- ASTM C303 - Standard Test Method for Dimensions and Density of Preformed Block and Board—Type Thermal Insulation
- ASTM C518 - Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus



- ASTM C578 - Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation
- ASTM C1338 - Standard Test Method for Determining Fungi Resistance of Insulation Materials and Facings
- ASTM C1512 - Standard Test Method for Characterizing the Effect of Exposure to Environmental Cycling on Thermal Performance of Insulation Products
- ASTM D1621 - Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- ASTM D1622 - Standard Test Method for Apparent Density of Rigid Cellular Plastics
- ASTM D2126 - Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- ASTM D2863 - Standard Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)
- ASTM D2842 - Standard Test Method for Water Absorption of Rigid Cellular Plastics
- ASTM E2178 - Standard Test Method for Air Permeance of Building Materials
- ASTM E84 - Standard Test Method for Surface Burning Characteristics of Building Materials
- ASTM E96 - Standard Test Methods for Water Vapor Transmission of Materials
- ASTM E119 - Standard Test Methods for Fire Tests of Building Construction and Material
- CAN/ULC-S101 - Standard Methods of Fire Endurance Tests of Building Construction and Materials
- CAN/ULC-S102 - Standard Method of Test for Surface Burning Characteristics of building Materials and Assemblies
- CAN/ULC-S701.1 - Standard for Thermal Insulation, Polystyrene, Boards & Pipe Covering
- ICC-ES AC12 - Foam Plastic Insulation
- NFPA 285 - Standard Fire Test Method for Evaluation of Fire Propagation Characteristics of Exterior Wall Assemblies Containing Combustible Components

TABLE 1. Airboard™ VB 250 Insulation + Vapor Barrier

Property <sup>1</sup>	Units	Value	Standard		
<b>Compressive Resistance</b> <sup>1,4</sup> Minimum @ 10% Deformation	psi	25	ASTM D1621 Proc. A	<sup>1</sup> The test methods used to determine the material properties provide a means of comparing different cellular plastic thermal insulations. They are intended for use in specifications, product evaluations and quality control but they are not intended to predict end-use product performance. <sup>2</sup> Values are for 1 inch or 25mm thick samples with laminated skins intact and seams, fasteners & penetrations properly sealed. Better values will result for thicker materials. <sup>3</sup> R means resistance to heat flow. The higher the R-value, the greater the insulating power. <sup>4</sup> The elastic limit is between 1% and 2% strain. Compressive resistances at 10% strain are provided for applications where the intended end-use can tolerate plastic (permanent) deformation under load. <sup>5</sup> The lab-test methods for water absorption use complete submersion under a head of water for 24 or 96 hours, so the values are applicable to specific design requirements only when the end-use conditions are similar to test method requirements. <sup>6</sup> not part of all the industry consensus standards (ASTM C578, CAN/ULC-S701) and provided AS-IS solely for informational purposes.	
	kPa	172			
<b>Thermal Resistance</b> <sup>1,2,3</sup> minimum at mean temperatures of:		25°F <sup>6</sup>	4.8		
	R-value / inch thickness	ft <sup>2</sup> •hr•°F/ (BTU•in)	40°F <sup>6</sup>		4.6
			75°F		4.27
			-4°C <sup>6</sup>		0.83
	R <sub>si</sub> / 25mm thickness	m <sup>2</sup> •°C/(W•25mm)	4°C <sup>6</sup>		0.80
		24°C	0.74		
<b>Air Permeance</b> <sup>2,6</sup> Tested at 1" thickness	CFM/ft <sup>2</sup> at 1.57 psf	0.0002	ASTM E2178		
	l/(s•m <sup>2</sup> ) at 75 Pa	0.001			
<b>Water Vapor Permeance</b> <sup>1,2</sup> Tested at 1" thickness	perm	0.03	ASTM E96 desiccant		
	ng/(Pa•s•m <sup>2</sup> )	1.5			
<b>Water Absorption</b> <sup>1,5</sup> Tested <u>with facers</u> at 1" thickness	% by volume	USA 0.3	ASTM C272, 1 day		
		Canada 0.7	ASTM D2842, 4 days		
<b>Dimensional Stability</b> <sup>1</sup>	% linear change max.	1.5	ASTM D2126, 7 days @ 70±2°C		
<b>EPS Flexural Strength</b> <sup>1</sup> Minimum <u>without facers</u>	psi	50	ASTM C203 Proc. B		
	kPa	345			

### Environment Data

EPS has much lower environmental impacts than most other foamed plastic insulation materials. The **Environmental Product Declaration (EPD)** has been certified by UL Environment and is available on [www.airfoam.com](http://www.airfoam.com).

Airboard™ EPS may contain up to 30% pre-consumer recycled content.

Airboard™ EPS **resists mold & fungi** growth per ASTM C1338 and has no nutritional value for insects. To protect against termites place adequate physical barriers such as membranes around below-grade EPS.

**Max. service temperature:** Long-Term Exposure 75°C [167°F]; Intermittent Exposure 80°C [176°F].

**Thermal expansion coefficient:** 5-7 • 10<sup>-5</sup>/°K

**Capillarity:** None.

### Fire Characteristics

- Limiting Oxygen Index: min. 24% per ASTM D2863. Airfoam's EPS for construction applications contains a polymeric (non-HBCD) flame-retardant modifier.

### Surface Burning Characteristics

- Canada:** CAN/ULC-S102.2: Flame-Spread Rating ≤290, Smoke Developed Classification over 500.
- USA:** ASTM E84 (UL 723)<sup>a</sup>: FSI ≤25, SDI ≤450 up to 6" thick.

<sup>a</sup> Ceiling measurement only, conducted through determination of flame spread index and smoke-developed index with the removal of any contribution of molten materials ignited on the floor of the Steiner tunnel.

### Fire Protection

**CAUTION:** This product is combustible. Keep away from high heat and ignition sources. A protective barrier or a thermal barrier is required as specified in the appropriate building code.

¾ Hour Fire Rating for a Composite Wall Assembly with EPS c.i. (Continuous Insulation) per **CAN/ULC-S101, ASTM E119**, see Design No. CPIA/CWP 45-01.

Meets **NFPA 285** with specific limitations for an exterior wall assembly.

For more information consult Airfoam's CRR-0379 at [www.airfoam.com/Airfoam-Code-Report-CCR-0379.pdf](http://www.airfoam.com/Airfoam-Code-Report-CCR-0379.pdf), your engineer, local building department or call Airfoam at 800.663.8162.

### Solubility & Incompatibility

Insoluble in water and in general chemically inert. EPS dissolves in hydrocarbons (e.g. fuels, oils, tar), organic solvents (e.g. acetone/ketones, benzene, paint thinner), ethers, esters, aldehydes and amines. The facers made of biaxially oriented polypropylene (BOPP) and polyethylene are incompatible with strong oxidizing agents, many hydrocarbons and aromatics.

## 5. INSTALLATION

Follow the Airboard™ Installation Guide available at [www.airboard.ca](http://www.airboard.ca).

Install Airboard™ insulation in compliance with all applicable building codes. Airboard™ insulation is easy to handle and install and can be cut with a utility knife or any sharp blade. Butt edges and ends tightly to adjacent Airboards. Ensure compatibility of any other product (such as adhesives, tapes, coatings or finishes) with Expanded Polystyrene and Airboard™ facers. Airboard™ Insulation is a non-structural material. Airboard™ Insulation shall only be placed into an assembly where the moisture transport mechanisms are well understood and determined to be acceptable in accordance with accepted engineering practice (e.g. current ASHRAE Handbook of Fundamentals).

For safe handling and storage information refer to the Safety Data Sheet (SDS) at [www.airfoam.com/SDS.pdf](http://www.airfoam.com/SDS.pdf) or request a printed copy.

**GHS Classification:** Non-Hazardous

**UV-Light Degradation:** Airboard™ Insulation can be exposed to direct sunlight for a few days. Prolonged exposure to ultraviolet light can degrade the facers and EPS.

**Please contact us for a free estimate or additional information: [www.airfoam.com](http://www.airfoam.com)**

**NOTICE:** Airfoam assumes no obligation or liability for the information in this document. Neither Airfoam nor its employees, representatives, or resellers make any representation or warranty, express or implied, whether arising by statute, operation of law, custom of trade or otherwise, with respect to the accuracy or completeness of information contained in this document or its fitness for any particular purpose, nor do they assume any liability for damages or injury resulting from the use of such information. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

**TABLE 2. Airboard™ 250 Thermal Resistance by Thickness**

Material Thickness	Performance @ 40°F [4°C]*		Minimum @ 75°F [24°C]*	
	R-Value ft <sup>2</sup> •hr•°F/BTU	R <sub>SI</sub> (m <sup>2</sup> •°C)/W	R-Value ft <sup>2</sup> •hr•°F/BTU	R <sub>SI</sub> (m <sup>2</sup> •°C)/W
1" 25.4mm	4.6	0.80	4.27	0.74
1.5" 38.1mm	6.9	1.20	6.41	1.11
2" 50.8mm	9.2	1.60	8.54	1.48
2.5" 63.5mm	11.5	2.00	10.68	1.85
3" 76.2mm	13.8	2.40	12.81	2.22
4" 101.6mm	18.4	3.20	17.08	2.96
5" 127mm	23.0	4.00	21.35	3.70
6" 152.4mm	27.6	4.80	25.62	4.44

\* Mean temperatures of the insulation, Minimum only applies when running air conditioning.

## 6. AVAILABILITY

Airboard™ is supplied from Surrey BC through our extensive distribution network. For product availability or to get in touch with your local distributor, call Airfoam at 800.663.8162 or +1.604.534.8626.

## 7. WARRANTY

Airfoam offers a limited product warranty for defective products. Please visit [www.airfoam.com/terms](http://www.airfoam.com/terms) for Terms and Conditions of Sale.

## 8. MAINTENANCE

No maintenance is required in normal use. EPS insulation that became wet can be dried out within reasonable times per ASTM C1512 tests using adequate drainage and/or ventilation.

## 9. TECHNICAL SERVICES

Airfoam can provide technical information and support to help address questions when using Airboard™ EPS Insulation. Technical personnel are available to assist with any insulation project. For technical assistance, contact Airfoam at:

Online: [www.airfoam.com/EPS-Insulation-Support.php](http://www.airfoam.com/EPS-Insulation-Support.php)

Phone: 800.663.8162 or +1.604.534.8626

Fax: +1.604.534.1212

## 10. FILING SYSTEM

Airboard™ Technical Specifications filed at: [www.airfoam.com](http://www.airfoam.com)



**Airfoam Industries Ltd.**

19402 - 56 Ave, Surrey BC V3S 6K4 Canada

800.663.8162 or 604.534.8626

[www.airfoam.com](http://www.airfoam.com)